



Bulletin	Order Item	Heat	PO No.	Shipping Mode	Order Dimensions	Slab Origin	TC No.
T121098	JSW20190-01	S31952	P0235349-11	TRUCK	0.625x96x240	JSW USA	T121098-1952-1

MELTED AND MANUFACTURED IN THE USA.
Part No.: DA106250962

Plates Certified for the Following grades	Specifications	Marking Instructions
ASTM-A36, ASME-SA36 AR Hot Rolled Carbon Steel Plates Plates Manufactured In the USA		Stencil in 1 location(s); X Loc. 18 Y Loc. 30; CUST; MADEINUSA PN PO; DIM GRADE; FREIGHT ORDERITEM PLATEID SHIPWEEK SLABID TRANSMODE Stamp in 1 location(s); X Loc. 18 Y Loc. 12; Slab ID; Slab ID
Sold To: SUPERIOR SUPPLY STEEL 318 S. CITIES SERVICE HWY. SULPHUR, LA 70663	Complies with ASTM A36 2019	
Ship To: SUPERIOR SUPPLY STEEL 318 N CITIES SERVICE HWY Sulphur, LA 70663		

Test	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn	Al	N	V	B	Ti	Nb	Ca	CE
LADLE	0.09	0.93	0.009	0.005	0.22	0.070	0.033	0.030	0.005	0.003	0.041	0.0108	0.003	0.0002	0.001	0.001	0.0020	0.26

Carbon Equivalent CE = C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15
 PCM = C + Si/30 + Mn/20 + Cu/20 + Ni/60 + Cr/20 + Mo/15 + V/10 + 5B
 AWS = C + (Mn+Si)/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

Plate Tested	Smpl. Loc.	Slab Identity	Gauge Tested	Test Cond	Test Dir.	Yield Point (KSI)	Ten. Stgth. (KSI)	Elong in 2"	YS/UTS Ratio	Yield Strength Determined At
1259813	A	07A	0.6250	AR	T	48	67	36.0%	0.72	0.2%
1259814	A	07B	0.6250	AR	T	50	67	36.0%	0.75	0.2%

Plates Certified For The Above Tests

Material	Thick(IN)	Width(IN)	Len(IN)	Wgt(LB)	Material	Thick(IN)	Width(IN)	Len(IN)	Wgt(LB)	Material	Thick(IN)	Width(IN)	Len(IN)	Wgt(LB)
1259813A	0.6250	96.000	240.00	4083.840	1259813B	0.6250	96.000	240.00	4083.840	1259813C	0.6250	96.000	240.00	4083.840
1259814A	0.6250	96.000	240.00	4083.840	1259814B	0.6250	96.000	240.00	4083.840					

DIN: EN 10204 2004 3.1 This is to certify that the product described herein was manufactured, sampled, and tested in accordance with the specifications and requirements in such specifications. Fine Grain, Si-Al Fully Killed Steel. We certify that delivery of this product with the requirement of the specification and purchase order received from customer. DRC Conflict Free. No intentional addition of Pb, Se, S, Hg or B.

April W





Bulletin	Order Item	Heat	PO No.	Shipping Mode	Order Dimensions	Slab Origin	TC No.
T121263	JSW20190-01	S31952	P0235349-11	TRUCK	0.625x96x240	JSW USA	T121263-1952-1

MELTED AND MANUFACTURED IN THE USA.
Part No.: DA106250962

Plates Certified for the Following grades	Specifications	Marking Instructions
ASTM-A36, ASME-SA36 AR		Stencil in 1 location(s); X Loc. 18 Y Loc. 30; CUST; MADEINUSA PN PO; DIM GRADE; FREIGHT ORDERITEM PLATEID SHIPWEEK SLABID TRANSMODE Stamp in 1 location(s); X Loc. 18 Y Loc. 12; Slab ID; Slab ID
Hot Rolled Carbon Steel Plates Plates Manufactured In the USA		

Sold To: SUPERIOR SUPPLY_STEEL 318 S. CITIES SERVICE HWY. SULPHUR, LA 70663	Complies with ASTM A36 2019
Ship To: SUPERIOR SUPPLY_STEEL 318 N CITIES SERVICE HWY Sulphur, LA 70663	

Test	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn	Al	N	V	B	Ti	Nb	Ca	CE
LADLE	0.09	0.93	0.009	0.005	0.22	0.070	0.033	0.030	0.005	0.003	0.041	0.0108	0.003	0.0002	0.001	0.001	0.0020	0.26

Carbon Equivalent CE = C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15
 PCM = C + Si/30 + Mn/20 + Cu/20 + Ni/60 + Cr/20 + Mo/15 + V/10 + 5B
 AWS = C + (Mn+Si)/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

Plate Tested	Smpl. Loc.	Slab Identity	Gauge Tested	Test Cond	Test Dir.	Yield Point (KSI)	Ten. Stgth. (KSI)	Elong in 2"	YS/UTS Ratio	Yield Strength Determined At
1259813	A	07A	0.6250	AR	T	48	67	36.0%	0.72	0.2%
1259814	A	07B	0.6250	AR	T	50	67	36.0%	0.75	0.2%

Plates Certified For The Above Tests

Material	Thick(IN)	Width(IN)	Len(IN)	Wgt(LB)
1259814C	0.6250	96.000	240.00	4083.840
1259815C	0.6250	96.000	240.00	4083.840
Material	Thick(IN)	Width(IN)	Len(IN)	Wgt(LB)
1259815A	0.6250	96.000	240.00	4083.840
1259815D	0.6250	96.000	240.00	4083.840
Material	Thick(IN)	Width(IN)	Len(IN)	Wgt(LB)
1259815B	0.6250	96.000	240.00	4083.840

DIN: EN 10204 2004 3.1 This is to certify that the product described herein was manufactured, sampled, and tested in accordance with the specifications and requirements in such specifications. Fine Grain, Si-Al Fully Killed Steel. We certify that delivery of this product with the requirement of the specification and purchase order received from customer. DRC Conflict Free. No intentional addition of Pb, Se, S, Hg or B.

Jackie Tamayo 281-383-5325 Jackie.Tamayo@jswsteel.us

