



CMC STEEL TEXAS  
1 STEEL MILL DRIVE  
SEGUIN TX 78155-7510

**CERTIFIED MILL TEST REPORT**

For additional copies call  
800-227-6489

We hereby certify that the test results presented here  
are accurate and conform to the reported grade specification

Rolando A Davila

Quality Assurance Manager

**1SERIES-BPS®**

HEAT NO.:2097216 SECTION: ANG 2 1/2 X 2 1/2x1/4 20"0" A36/52950 GRADE: ASTM A36-19/A529-14 Gr 50 ROLL DATE: 09/16/2022 MELT DATE: 07/18/2022 Cert. No.: 85177857 / 097216A397	S O L D T O	Superior Supply & Steel Co 318 N Cities Service Hwy Sulphur LA US 70663-5424 3376252300 3376258509	S H I P T O	Superior Supply & Steel 318 City Service Highway Sulphur LA US 70663-0000 3376252300 3376258509	Delivery#: 85177857 BOL#: 74993451 CUST PO#: 235953-11 CUST P/N: DLVRY LBS / HEAT: 4592.000 LB DLVRY PCS / HEAT: 56 EA
---	----------------------------	---	----------------------------	--	---

Characteristic	Value	Characteristic	Value	Characteristic	Value
C	0.14%	Elongation Gage Lgth test 1	8IN	<p><b>The Following is true of the material represented by this MTR:</b></p> <p><i>*Material is fully killed and is Hot Rolled Steel</i></p> <p><i>*100% melted, rolled, and manufactured in the USA</i></p> <p><i>*EN10204:2004 3.1 compliant</i></p> <p><i>*Contains no weld repair</i></p> <p><i>*Contains no Mercury contamination</i></p> <p><i>*Manufactured in accordance with the latest version of the plant quality manual</i></p> <p><i>*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661</i></p> <p><i>*Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to <a href="http://www.P65Warnings.ca.gov">www.P65Warnings.ca.gov</a></i></p>	
Mn	0.65%	Yield to tensile ratio test1	0.76		
P	0.007%	Yield Strength test 2	55.5ksi		
S	0.020%	Tensile Strength test 2	75.7ksi		
Si	0.21%	Elongation test 2	26%		
Cu	0.35%	Elongation Gage Lgth test 2	8IN		
Cr	0.18%	Yield to tensile ratio test2	0.73		
Ni	0.18%	C+(Mn/6)	0.25%		
Mo	0.044%				
V	0.000%				
Cb	0.010%				
Sn	0.011%				
Al	0.002%				
B	0.0001%				
Ti	0.001%				
N	0.0040%				
Carbon Eq A529	0.37%				
Yield Strength test 1	59.0ksi				
Tensile Strength test 1	77.7ksi				
Elongation test 1	24%				

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W