

REF.B/L: 81150917
 Date: 04/27/2023
 Customer: 1592



Atlas Tube Alabama
 171 Cleage Dr
 Birmingham Alabama USA
 35217

Tel:
 Fax:

MATERIAL TEST REPORT

Shipped To

Superior Supply and Steel
 318 North Cities Service Hwy
 SULPHUR LA 70663
 USA

Sold To

Superior Supply and Steel
 PO Box 2388
 SULPHUR LA 70664
 USA

Material: 3.0x3.0x250x20'2"0(5x5). **Material No:** 30030250 **Made in:** USA
Sales Order: 1894163 **Purchase Order:** P0240203-01 **Melted and Poured in:** USA
Heat No: SN2293 **Heat:** C **Mn:** 0.400 **P:** 0.006 **S:** 0.004 **Si:** 0.035 **Al:** 0.027 **Cu:** 0.150 **Cb:** 0.000 **Mo:** 0.020 **Ni:** 0.040 **Cr:** 0.050 **V:** 0.003 **Ti:** 0.002 **B:** 0.0000 **N:** 0.0060 **Ca:** 0.0020
Bundle No: MA00157342 **PCs:** 25 **Yield:** 068373 Psi **Tensile:** 076071 Psi **EIn.2in:** 25.4% **Method:** EAF **Recycled Content:** 53.70% **Post Consumer:** 23.80% **Pre-Consumer (Post Industrial):** 29.90% **% Harvested:** 86% **Within Miles of Location:** 500
Heat: SN2293 **MILL:** NUCOR **Decatur,AL**

Material: 3.0x3.0x250x20'2"0(5x5). **Material No:** 30030250 **Made in:** USA
Sales Order: 1894163 **Purchase Order:** P0240203-01 **Melted and Poured in:** USA
Heat No: SN2293 **Heat:** C **Mn:** 0.400 **P:** 0.006 **S:** 0.004 **Si:** 0.035 **Al:** 0.027 **Cu:** 0.150 **Cb:** 0.000 **Mo:** 0.020 **Ni:** 0.040 **Cr:** 0.050 **V:** 0.003 **Ti:** 0.002 **B:** 0.0000 **N:** 0.0060 **Ca:** 0.0020
Bundle No: MA00157343 **PCs:** 25 **Yield:** 068373 Psi **Tensile:** 076071 Psi **EIn.2in:** 25.4% **Method:** EAF **Recycled Content:** 53.70% **Post Consumer:** 23.80% **Pre-Consumer (Post Industrial):** 29.90% **% Harvested:** 86% **Within Miles of Location:** 500
Heat: SN2293 **MILL:** NUCOR **Decatur,AL**

Authorized by Quality Assurance *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

