

Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81143971  
 Date: 03/21/2023  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

**Material:** 1.5x1.5x250x20'0"0(10x5). **Material No:** 0150152502000-B **Made in:** USA  
**Sales Order:** 1879646 **Purchase Order:** P0238998-11 **Melted and Poured in:** USA  
**Cust Material#:** 982024289

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
B300729	0.070	0.380	0.008	0.002	0.020	0.029	0.080	0.000	0.010	0.030	0.050	0.000	0.001	0.0001	0.0076	0.0016

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.16		
MC00202367	50	071043 Psi	078777 Psi	28.2 %	ASTM A500-21 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
B300729	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:  
 Sales Or. Note:

**Material:** 2.5x2.5x250x20'0"0(5x5). **Material No:** 0250252502000-B **Made in:** USA  
**Sales Order:** 1883617 **Purchase Order:** P0239523-11 **Melted and Poured in:** USA  
**Cust Material#:** 982024340

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
NN0961	0.190	0.400	0.010	0.003	0.043	0.027	0.110	0.000	0.010	0.030	0.060	0.002	0.002	0.0000	0.0070	0.0020

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.29		
MC00202714	25	070919 Psi	086179 Psi	28.9 %	ASTM A500-21 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
NN0961	NUCOR	Decatur,AL	EAF	53.70%	23.80%	29.90%	86%	500

Material Note:  
 Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. This document is in compliance with the requirements of EN 10204 type 3.1

