



CMC STEEL TEXAS  
1 STEEL MILL DRIVE  
SEGUIN TX 78155-7510

1SERIES-BPS<sup>®</sup>

**CERTIFIED MILL TEST REPORT**

For additional copies call  
830-372-8771

We hereby certify that the test results presented here  
are accurate and conform to the reported grade specification

Rolando A Davila

Quality Assurance Manager

HEAT NO.: 1077968 SECTION: ANG 3 X 3x3/16 20'0" A36/52950 GRADE: ASTM A36-19/A529-14 Gr 50 ROLL DATE: 02/15/2022 MELT DATE: 01/22/2022 Cert. No.: 83753641 / 077968A908		S O L D T O 318 N Cities Service Hwy Sulphur LA US 70663-5424 3376252300 3376258509		S H I P T O 318 City Service Highway Sulphur LA US 70663-0000 3376252300 3376258509		Delivery#: 83753641 BOL#: 74619324 CUST PO#: 231535-11 CUST P/N: DLVRY LBS / HEAT: 4674.000 LB DLVRY PCS / HEAT: 63 EA	
Characteristic Value C 0.16% Mn 0.61% P 0.015% S 0.033% Si 0.17% Cu 0.49% Cr 0.12% Ni 0.15% Mo 0.043% V 0.004% Cb 0.010% Sn 0.013% B 0.0003% Ti 0.001% N 0.0098% Carbon Eq A6 0.33% Carbon Eq A529 0.36% Yield Strength test 1 57.8ksi Tensile Strength test 1 75.9ksi		Characteristic Value Elongation test 1 26% Elongation Gage Lgth test 1 8IN Yield to tensile ratio test1 0.76 Yield Strength test 2 58.2ksi Tensile Strength test 2 75.3ksi Elongation test 2 25% Elongation Gage Lgth test 2 8IN Yield to tensile ratio test2 0.77		Characteristic Value The Following is true of the material represented by this MTR: *Material is fully killed *100% melted and rolled in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov			

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W