



Atlas Tube Alabama
 171 Cleage Dr
 Birmingham Alabama USA
 35217
 Tel:
 Fax:

REF.B/L: 81170088
 Date: 08/22/2023
 Customer: 1592

MATERIAL TEST REPORT

Shipped To
 Superior Supply and Steel
 318 North Cities Service Hwy
 SULPHUR LA 70663
 USA

Sold To
 Superior Supply and Steel
 PO Box 2388
 SULPHUR LA 70664
 USA

Material: 2.0X2.0X250X20"0"(6x6). **Material No:** 0200202502000-B **Made in:** USA
Sales Order: 1944126 **Purchase Order:** P0243508-01 **Melted and Poured in:** USA
Heat No: SN4661 **C:** 0.190 **Mn:** 0.380 **P:** 0.006 **S:** 0.004 **Si:** 0.022 **Al:** 0.034 **Cu:** 0.120 **Cr:** 0.040 **Ni:** 0.040 **Mo:** 0.010 **Co:** 0.000 **Ti:** 0.000 **B:** 0.000 **N:** 0.0050 **Ca:** 0.0020
Bundle No: MC00215295 **PCs:** 36 **Yield:** 057219 Psi **Tensile:** 068880 Psi **Eln.2in:** 28.3 % **Certification:** ASTM A500-21 GRADE B&C **CE: 0.28**
Heat MILL: NUCOR **Mill Location:** Decatur,AL **Method:** EAF **Recycled Content:** 53.70% **Post Consumer:** 23.80% **Pre-Consumer (Post Industrial):** 29.90% **% Harvested:** 86% **Within Miles of Location:** 500
Material Note:
Sales Or. Note:

Material: 3.0X3.0X120X20"0"(5x5). **Material No:** 0300301202000-B **Made in:** USA
Sales Order: 1944126 **Purchase Order:** P0243508-01 **Melted and Poured in:** USA
Heat No: NN3011 **C:** 0.190 **Mn:** 0.390 **P:** 0.006 **S:** 0.004 **Si:** 0.033 **Al:** 0.030 **Cu:** 0.120 **Cr:** 0.080 **Ni:** 0.030 **Mo:** 0.010 **Co:** 0.002 **Ti:** 0.002 **B:** 0.0000 **N:** 0.0060 **Ca:** 0.0020
Bundle No: MA00162065 **PCs:** 25 **Yield:** 091701 Psi **Tensile:** 101463 Psi **Eln.2in:** 25.1 % **Certification:** ASTM A500-21 GRADE B&C **CE: 0.29**
Heat MILL: NUCOR **Mill Location:** Decatur,AL **Method:** EAF **Recycled Content:** 53.70% **Post Consumer:** 23.80% **Pre-Consumer (Post Industrial):** 29.90% **% Harvested:** 86% **Within Miles of Location:** 500
Material Note:
Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

