



CMC STEEL TEXAS
1 STEEL MILL DRIVE
SEGUIN TX 78155-7510

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-6489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Draw M Fischer
Draw M Fischer

Quality Assurance Manager

1 SERIES-BPS

HEAT NO.:3125925	S	Superior Supply & Steel Co	S	Superior Supply	Delivery#: 85640500
SECTION: ANG 2 X 2x3/16 20'0"	O		H	1948 Grand Caillou Rd	BOL#: 75714287
A36/52950	L	318 N CITIES SERVICE HWY	I	Houma LA	CUST PO#: PO245955-15
GRADE: ASTM A36-19/A529-19 Gr 50	D	SULPHUR LA	P	US 70363-7085	CUST P/N:
ROLL DATE: 11/18/2023	T	US 70663-5424	T	9852740111	DLVRY LBS / HEAT: 4685.000 LB
MELT DATE: 10/04/2023	O	3376252300	O		DLVRY PCS / HEAT: 96 EA
Cert. No.: 85640500 / 125925A111		3376258509			

Characteristic	Value	Characteristic	Value	Characteristic	Value
C	0.08%	Tensile Strength test 2	71.5ksi	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov	
Mn	0.85%	Elongation test 2	30%		
P	0.010%	Elongation Gage Lgth test 2	8IN		
S	0.023%				
Si	0.17%				
Cu	0.36%				
Cr	0.08%				
Ni	0.12%				
Mo	0.047%				
V	0.000%				
Cb	0.014%				
Sn	0.010%				
Al	0.001%				
Carbon Eq A529	0.31%				
Yield Strength test 1	55.5ksi				
Tensile Strength test 1	71.6ksi				
Elongation test 1	29%				
Elongation Gage Lgth test 1	8IN				
Yield Strength test 2	55.9ksi				

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W