

Atlas Tube Corp. Kansas City  
 Burlington St  
 North Kansas City Missouri USA  
 64116  
 Tel:  
 Fax:

**Atlas Tube**  
 A DIVISION OF ZEKELMAN INDUSTRIES

REF. B/L: 81181275  
 Date: 10/24/2023  
 Customer: 1592

**Sold To**  
 Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**  
 Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

**MATERIAL TEST REPORT**

Material: 4.0x4.0x375x20"0(5x4) Material No: 400403752000 Made in: USA

Sales Order: 1966471 Purchase Order: P0244897-01 Melted and Poured in: USA

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
17054D	0.220	0.340	0.006	0.011	0.004	0.048	0.050	0.000	0.010	0.020	0.060	0.000	0.000	0.0000	0.0030	0.0000
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Tensile</b>	<b>Eln.2in</b>	<b>Certification</b>	<b>CE: 0.30</b>										
Z200017705	20	053021 Psi	064801 Psi	34.5 %	ASTM A500-21 GRADE B&C											
Heat	MILL	Mill Location		Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location							
17054D	USSTEEL	GRANITE CITY,IL		BOF	36.90%	19.80%	14.40%	100%	500							

Material: 5.0x5.0x375x20"0(4x3) Material No: 500503752000 Made in: USA

Sales Order: 1961224 Purchase Order: P0244481-01 Melted and Poured in: USA

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
18111C	0.210	0.350	0.006	0.008	0.007	0.044	0.030	0.002	0.000	0.020	0.040	0.000	0.001	0.0000	0.0040	0.0000
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Tensile</b>	<b>Eln.2in</b>	<b>Certification</b>	<b>CE: 0.28</b>										
Z200019692	12	057004 Psi	069960 Psi	36.0 %	ASTM A500-21 GRADE B&C											
Heat	MILL	Mill Location		Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location							
18111C	USSTEEL	GRANITE CITY,IL		BOF	36.90%	19.80%	14.40%	100%	500							

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

