

Atlas Tube Alabama
 171 Cleage Dr
 Birmingham Alabama USA
 35217
 Tel:
 Fax:



REF.B/L: 81223679
 Date: 05/24/2024
 Customer: 1592

MATERIAL TEST REPORT

Sold To

Superior Supply and Steel
 PO Box 2388
 SULPHUR LA 70664
 USA

Shipped To

Superior Supply and Steel
 318 North Cities Service Hwy
 SULPHUR LA 70663
 USA

Material:	2.0x2.0x250x20'0"0(6x6).											Material No:	0200202502000-B			Made in:	USA		
Sales Order:	2050914											Purchase Order:	P0249265-01			Melted and Poured in:	USA		
Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca			
A404991	0.200	0.460	0.012	0.003	0.020	0.028	0.090	0.001	0.020	0.050	0.070	0.000	0.001	0.0001	0.0067	0.0021			
Bundle No	PCs	Yield	Tensile	Fln.2in	Certification							CE: 0.31							
MC00235906	36	073592 Psi	082736 Psi	26.2 %	ASTM A500-23 GRADE B&C														
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location											
A404991	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500											
Material Note:																			
Sales Or. Note:																			

Material:	4.0x4.0x120x20'0"0(4x3).											Material No:	0400401202000-B			Made in:	USA		
Sales Order:	2041619											Purchase Order:	P0248163-01			Melted and Poured in:	USA		
Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca			
A403041	0.210	0.470	0.008	0.004	0.020	0.024	0.110	0.000	0.020	0.040	0.050	0.001	0.001	0.0001	0.0063	0.0021			
Bundle No	PCs	Yield	Tensile	Fln.2in	Certification							CE: 0.32							
MA00182872	12	062426 Psi	066515 Psi	26.7 %	ASTM A500-23 GRADE B&C														
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location											
A403041	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500											
Material Note:																			
Sales Or. Note:																			

Authorized by Quality Assurance *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

