

Sold To: SUPERIOR SUPPLY & STEEL  
 PO BOX 2388  
 SULPHUR, LA 70664 US

Ship To: SUPERIOR SUPPLY  
 318 CITIES SERVICE HWY  
 HWY-108  
 SULPHUR, LA 70663 US

Customer PO	P0255010-01	Sales Order #	11082829 - 6.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3005593
Grade	A36/A529 Gr 50, CSA 44W/50W	Lot #	110006640362
Size	2" x 2" x 0.25"	Heat #	1100066403
BOL #	BOL-1953260	Load #	1910530
Description	Hot Roll - Merchant Bar Quality Equal Angle 2" x 2" x 1/4" A36/A529 Gr 50, CSA 44W/50W 20' 0" [240"] 2001-6000 lbs	Customer Part #	
Production Date	02/27/2025	Qty Shipped LBS	5168
Product Country Of Origin	United States	Qty Shipped EA	81
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

Melt Country of Origin : United States

Melting Date: 02/20/2025

Roll Country of Origin : United States

Rolling Date: 02/26/2025

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	Cr (%)	Mo (%)	Cu (%)	V (%)	Nb (%)
0.11	0.83	0.011	0.018	0.218	0.11	0.18	0.04	0.26	0.032	0.002

Reduction Ratio 41.59 : 1

**Tensile testing**

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	56700	73500	28.0
(2)	55500	72900	30.0

**Comments:**

MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/A529-05 GR50(345); A572/572M-07 GR50(345); A709/A709M-10 GR36(250); CSA G40.21-04 GR44W(300W)&GR50W(350W); AASHTO M270/270M-10 GR36(270); ASME SA36/SA36M-10; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
2. Mercury not intentionally added at any point during manufacturing or testing of this material.
3. Welding or weld repair was not performed on this material.
4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
5. Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.

