

Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81287986  
 Date: 04/04/2025  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

**Material:** 4.0x2.0x250x20'0"0(5x5). **Material No:** 400202502000 **Made in:** USA  
**Sales Order:** 2161252 **Purchase Order:** P0255275-01 **Melted and Poured in:** USA  
**Cust Material#:** 982024750

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
B502607	0.220	0.490	0.007	0.001	0.020	0.028	0.090	0.001	0.010	0.040	0.070	0.001	0.001	0.0000	0.0056	0.0022

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.33		
MA00211065	25	075123 Psi	078509 Psi	24.4 %	ASTM A500-23 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
B502607	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:

Sales Or. Note:

**Material:** 4.0x2.0x250x20'0"0(5x5). **Material No:** 400202502000 **Made in:** USA  
**Sales Order:** 2161275 **Purchase Order:** P0255279-08 **Melted and Poured in:** USA  
**Cust Material#:** 982024750

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
B502607	0.220	0.490	0.007	0.001	0.020	0.028	0.090	0.001	0.010	0.040	0.070	0.001	0.001	0.0000	0.0056	0.0022

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.33		
MA00211063	25	075123 Psi	078509 Psi	24.4 %	ASTM A500-23 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
B502607	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:

Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act. Method of manufacture is ERW.



Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81287986  
 Date: 04/04/2025  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

**Material:** 1.5x1.5x120x20'0"0(8x8).A513      **Material No:** 0150151202000-A513      **Made in:** USA  
**Sales Order:** 2161275      **Purchase Order:** P0255279-08      **Melted and Poured in:** USA  
**Cust Material#:** 982024200

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
B503853	0.060	0.350	0.013	0.003	0.020	0.022	0.100	0.001	0.010	0.040	0.060	0.000	0.001	0.0000	0.0068	0.0016

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.15		
MC00266720	64	000000 Psi	000000 Psi	%	ASTM A513-24, TYPE 1			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
B503853	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:

Sales Or. Note:

**Material:** 1.5x1.5x120x24'0"0(8x8).A513      **Material No:** 0150151202400-A513      **Made in:** USA  
**Sales Order:** 2165093      **Purchase Order:** P0255277-01      **Melted and Poured in:** USA  
**Cust Material#:** 982024201

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
B503851	0.060	0.370	0.016	0.004	0.020	0.027	0.110	0.001	0.010	0.040	0.070	0.000	0.001	0.0000	0.0071	0.0019

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.15		
MC00266604	64	000000 Psi	000000 Psi	%	ASTM A513-24, TYPE 1			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
B503851	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:

Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act. Method of manufacture is ERW.



Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81287986  
 Date: 04/04/2025  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

**Material:** 3.0x3.0x250x20'0"0(5x5). **Material No:** 0300302502000-B **Made in:** USA  
**Sales Order:** 2161275 **Purchase Order:** P0255279-08 **Melted and Poured in:** USA  
**Cust Material#:** 982024560

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
B502609	0.210	0.460	0.007	0.003	0.020	0.028	0.090	0.001	0.020	0.040	0.070	0.001	0.001	0.0001	0.0072	0.0020

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.32		
MA00210978	25	072995 Psi	081760 Psi	24.0 %	ASTM A500-23 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
B502609	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:  
 Sales Or. Note:

**Material:** 3.0x3.0x250x20'0"0(5x5). **Material No:** 0300302502000-B **Made in:** USA  
**Sales Order:** 2165093 **Purchase Order:** P0255277-01 **Melted and Poured in:** USA  
**Cust Material#:** 982024560

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
B502607	0.220	0.490	0.007	0.001	0.020	0.028	0.090	0.001	0.010	0.040	0.070	0.001	0.001	0.0000	0.0056	0.0022

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.33		
MA00210981	25	067783 Psi	079175 Psi	24.1 %	ASTM A500-23 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
B502607	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:  
 Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act. Method of manufacture is ERW.



Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81287986  
 Date: 04/04/2025  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

<b>Material:</b>	3.0x3.0x250x20'0"0(5x5).										<b>Material No:</b>	0300302502000-B			<b>Made in:</b>	USA		
<b>Sales Order:</b>	2174157										<b>Purchase Order:</b>	P0255798-01			<b>Melted and Poured in:</b>	USA		
<b>Cust Material#:</b>	982024560																	
<b>Heat No</b>	<b>C</b>	<b>Mn</b>	<b>P</b>	<b>S</b>	<b>Si</b>	<b>Al</b>	<b>Cu</b>	<b>Cb</b>	<b>Mo</b>	<b>Ni</b>	<b>Cr</b>	<b>V</b>	<b>Ti</b>	<b>B</b>	<b>N</b>	<b>Ca</b>		
NQ0625	0.200	0.400	0.014	0.002	0.023	0.024	0.190	0.000	0.010	0.050	0.070	0.002	0.001	0.0000	0.0070	0.0030		
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Tensile</b>	<b>Fln.2in</b>	<b>Certification</b>						<b>CE: 0.30</b>							
MA00210932	25	072467 Psi	081886 Psi	24.3 %	ASTM A500-23 GRADE B&C													
<b>Heat</b>	<b>MILL</b>	<b>Mill Location</b>	<b>Method</b>	<b>Recycled Content</b>	<b>Post Consumer</b>	<b>Pre-Consumer (Post Industrial)</b>	<b>% Harvested</b>	<b>Within Miles of Location</b>										
NQ0625	NUCOR	Decatur,AL	EAF	53.70%	23.80%	29.90%	86%	500										
<b>Material Note:</b>																		
<b>Sales Or. Note:</b>																		

<b>Material:</b>	3.0x3.0x250x20'0"0(5x5).										<b>Material No:</b>	0300302502000-B			<b>Made in:</b>	USA		
<b>Sales Order:</b>	2161275										<b>Purchase Order:</b>	P0255279-08			<b>Melted and Poured in:</b>	USA		
<b>Cust Material#:</b>	982024560																	
<b>Heat No</b>	<b>C</b>	<b>Mn</b>	<b>P</b>	<b>S</b>	<b>Si</b>	<b>Al</b>	<b>Cu</b>	<b>Cb</b>	<b>Mo</b>	<b>Ni</b>	<b>Cr</b>	<b>V</b>	<b>Ti</b>	<b>B</b>	<b>N</b>	<b>Ca</b>		
B502607	0.220	0.490	0.007	0.001	0.020	0.028	0.090	0.001	0.010	0.040	0.070	0.001	0.001	0.0000	0.0056	0.0022		
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Tensile</b>	<b>Fln.2in</b>	<b>Certification</b>						<b>CE: 0.33</b>							
MA00210979	15	067783 Psi	079175 Psi	24.1 %	ASTM A500-23 GRADE B&C													
<b>Heat</b>	<b>MILL</b>	<b>Mill Location</b>	<b>Method</b>	<b>Recycled Content</b>	<b>Post Consumer</b>	<b>Pre-Consumer (Post Industrial)</b>	<b>% Harvested</b>	<b>Within Miles of Location</b>										
B502607	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500										
<b>Material Note:</b>																		
<b>Sales Or. Note:</b>																		

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act. Method of manufacture is ERW.



Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81287986  
 Date: 04/04/2025  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

**Material:** 3.0x3.0x250x20'0"0(5x5). **Material No:** 0300302502000-B **Made in:** USA  
**Sales Order:** 2161275 **Purchase Order:** P0255279-08 **Melted and Poured in:** USA  
**Cust Material#:** 982024560

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
B502609	0.210	0.460	0.007	0.003	0.020	0.028	0.090	0.001	0.020	0.040	0.070	0.001	0.001	0.0001	0.0072	0.0020

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.32		
MA00210979	10	072995 Psi	081760 Psi	24.0 %	ASTM A500-23 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
B502609	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:

Sales Or. Note:

**Material:** 3.0x3.0x250x20'0"0(5x5). **Material No:** 0300302502000-B **Made in:** USA  
**Sales Order:** 2161275 **Purchase Order:** P0255279-08 **Melted and Poured in:** USA  
**Cust Material#:** 982024560

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
NQ0625	0.200	0.400	0.014	0.002	0.023	0.024	0.190	0.000	0.010	0.050	0.070	0.002	0.001	0.0000	0.0070	0.0030

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.30		
MA00210933	25	072467 Psi	081886 Psi	24.3 %	ASTM A500-23 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
NQ0625	NUCOR	Decatur,AL	EAF	53.70%	23.80%	29.90%	86%	500

Material Note:

Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act. Method of manufacture is ERW.



Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81287986  
 Date: 04/04/2025  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

**Material:** 3.0x3.0x250x20'0"0(5x5). **Material No:** 0300302502000-B **Made in:** USA  
**Sales Order:** 2165093 **Purchase Order:** P0255277-01 **Melted and Poured in:** USA  
**Cust Material#:** 982024560

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
32500955	0.210	0.870	0.005	0.004	0.020	0.031	0.130	0.000	0.010	0.040	0.050	0.002	0.001	0.0003	0.0093	0.0018

Bundle No	PCs	Yield	Tensile	El.2in	Certification	CE: 0.38		
MA00213635	25	059705 Psi	076083 Psi	27.0 %	ASTM A500-23 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
32500955	BIGRIVER	Osceola,AR	EAF	76.00%	95.00%	5.00 %	75%	500

**Material Note:**  
**Sales Or. Note:**

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act. Method of manufacture is ERW.

