Date: 2/23/2022 Heat#: 1100031695*

Tag: T35022322



Mill Certification

02/18/2022

MTR#:955801-3 Lot #:110003169520 8812 HWY 79 W Jewett, TX 75846 US 903 626-4461 Fax: 903 626-6290

OUT THE OFFICE STEEL WAREHOUSE

Customer PO	ssw125901	Sales Order #	11042335 - 23.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3016667
Grade	A36/A529 Gr 50, CSA 44W/50W	Lot #	110003169520
Size	0.375" x 2"	Heat #	1100031695
BOL#	BOL-1052999	Load #	955801
Description	Hot Roll - Merchant Bar Quality Flat 3/8" x 2" A36/A529 Gr 50, CSA 44W/50W 20' 0" [240"] 4001-8000 lbs	Customer Part #	
Production Date	01/17/2022	Qty Shipped LBS	10412
Product Country Of Origin	United States	Qty Shipped EA	204
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements. Melting Date: 01/16/2022 Melt Country of Origin: United States Nb (%) V (%) Cr (%) Mo (%) Cu (%) Mn (%) P(%) S (%) SI (%) Ni (%) C (%) 0.001 0.034 0.26 0.014 0.209 0.13 0.14 0.07 0.010 0.12 0.86

Reduction Ratio 51.98:1

Tensile testina

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	55100	72200	25.0
(2)	55200	72900	25.0

MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/A529-05 GR50(345); A572/572M-07 GR50(345); A709/A709M-10 GR36(250); CSA G40.21-04 GR44W(300W)&GR50W(350W); AASHTO M270/270M-10 GR36(270); ASME SA36/SA36M-10; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

- 1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
- 2. Mercury not intentionally added at any point during manufacturing or testing of this material.
- 3. Welding or weld repair was not performed on this material.
- 4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor
- 5. Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.

Robert Fortson, Quality Assurance

Page 1 of 1