

CMC STEEL TEXAS 1 STEEL MILL DRIVE **SEGUIN TX 78155-7510**

CERTIFIED MILL TEST REPORT

For additional copies call 800-227-6489

We hereby certify that the test results presented here are accurate and conform to the reported grade specification

Rolando A Davila

Quality Assurance Manager

HEAT NO.:3118024

SECTION: REBAR 13MM (#4) 20'0" 420/60

GRADE: ASTM A615-20 Gr 420/60

ROLL DATE: 09/01/2022 MELT DATE: 09/01/2022

Cert. No.: 85171216 / 118024A130

S	Superior Supply & Steel Co
0	
L	318 N Cities Service Hwy
D	Sulphur LA US 70663-5424
	US 70663-5424
Т	3376252300
0	3376258509

S	Superior Supply & Steel
Н	
I	318 City Service Highway
Ρ	Sulphur LA
	US 70663-0000
Т	318 City Service Highway Sulphur LA US 70663-0000 3376252300 3376258509
0	3376258509

Delivery#: 85171216 BOL#: 74984192 CUST PO#: 235805-11 CUST P/N:

DLVRY LBS / HEAT: 4382.000 LB DLVRY PCS / HEAT: 328 EA

Characteristic	Value	Characteristic	Value	Characteristic Value
С	0.44%			
Mn	0.87%			
P	0.011%			
S	0.038%			
Si	0.17%			
Cu	0.37%			
Cr	0.08%			
Ni	0.17%			
Мо	0.062%			The Following is true of the material represented by this MTR:
V	0.000%			*Material is fully killed and is Hot Rolled Steel
Cb	0.001%			*100% melted, rolled, and manufactured in the USA
Sn	0.009%			*EN10204:2004 3.1 compliant
Al	0.000%			*Contains no weld repair
Yield Strength test 1	68.8ksi			*Contains no Mercury contamination
Tensile Strength test 1	106.8ksi			*Manufactured in accordance with the latest version
Elongation test 1	14%			of the plant quality manual
Elongation Gage Lgth test 1	8IN			*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661
Tensile to Yield ratio test1	1.55			*Warning: This product can expose you to chemicals which are
Bend Test 1	Passed			known to the State of California to cause cancer, birth defects
Bend Test Diameter	1.750IN			or other reproductive harm. For more information go
				to www.P65Warnings.ca.gov

REMARKS: