

CMC STEEL TEXAS

1 STEEL MILL DRIVE
SEGUIN TX 78155-7510

CERTIFIED MILL TEST REPORT

For additional copies call 800-227-6489

We hereby certify that the test results presented here are accurate and conform to the reported grade specification

Rolando A Davila

Quality Assurance Manager

1SERIES-BPS ®

HEAT NO.:3116796

SECTION: FLAT 1/4x4 20'0" A36/52950 GRADE: ASTM A36-19/A529-19 GR 50

ROLL DATE: 07/17/2022 MELT DATE: 07/14/2022

Cert. No.: 85176676 / 116796A934

50 D S

0

L

318 N Cities Service Hwy Sulphur LA

Superior Supply & Steel Co

US 70663-5424 T 3376252300 O 3376258509 S Superior Steel
H
I 217 Darnall Rd
P New Iberia LA
US 70560-0781
T 8002529017

Delivery#: 85176676 BOL#: 74992208 CUST PO#: 235954-11

CUST P/N:

DLVRY LBS / HEAT: 8976.000 LB DLVRY PCS / HEAT: 132 EA

Characteristic	Value	Characteristic	Value	Characteristic Value
С	0.10%	Tensile Strength test 2	76.1ksi	
Mn	1.02%	Elongation test 2	29%	
Р	0.015%	Elongation Gage Lgth test 2	8IN	
S	0.038%			
Si	0.21%			
Cu	0.30%			
Cr	0.11%			
Ni	0.14%			
Мо	0.037%			The Following is true of the material represented by this MTR:
V	0.000%			*Material is fully killed and is Hot Rolled Steel
Cb	0.015%			*100% melted, rolled, and manufactured in the USA
Sn	0.009%			*EN10204:2004 3.1 compliant
Al	0.001%			*Contains no weld repair
Carbon Eq F1554	0.29%			*Contains no Mercury contamination
Carbon Eq A529	0.37%			*Manufactured in accordance with the latest version
Yield Strength test 1	54.2ksi			of the plant quality manual
Tensile Strength test 1	75.9ksi			*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661
Elongation test 1	27%			*Warning: This product can expose you to chemicals which are
Elongation Gage Lgth test 1	8IN			known to the State of California to cause cancer, birth defects
Yield Strength test 2	55.5ksi			or other reproductive harm. For more information go
				to www.P65Warnings.ca.gov

0

REMARKS: ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W