

## CMC STEEL TEXAS 1 STEEL MILL DRIVE SEGUIN TX 78155-7510

S

0

L

T 0

## **CERTIFIED MILL TEST REPORT**

For additional copies call 800-227-6489

## We hereby certify that the test results presented here are accurate and conform to the reported grade specification

Rolando A Davila

## **Quality Assurance Manager**

HEAT NO.:3115038

SECTION: ANG 1 1/2 X 1 1/2x3/16 20'0"

A36/52950

GRADE: ASTM A36-19A529-14 GR 50

ROLL DATE: 06/29/2022 MELT DATE: 05/05/2022

Cert. No.: 85180719 / 115038A117

Superior Supply & Steel Co

318 N Cities Service Hwy
Sulphur LA
US 70663-5424
3376252300
3376258509

S Superior Supply & Steel
H
I 318 City Service Highway
P Sulphur LA
US 70663-0000
T 3376252300

3376258509

Delivery#: 85180719 BOL#: 74997537 CUST PO#: 236408-11 CUST P/N:

DLVRY LBS / HEAT: 4680.000 LB

DLVRY PCS / HEAT: 130 EA

Characteristic	Value	Characteristic	Value	Characteristic Val	lue
С	0.17%	Elongation test 2	29%		
Mn	0.70%	Elongation Gage Lgth test 2	8IN		
P	0.013%				
S	0.033%				
Si	0.22%				
Cu	0.44%				
Cr	0.12%				
Ni	0.26%				
Мо	0.037%			The Following is true of the material represented	by this MTR:
V	0.000%			*Material is fully killed and is Hot Rolled Steel	
Cb	0.001%			*100% melted, rolled, and manufactured in the USA	
Sn	0.012%			*EN10204:2004 3.1 compliant	
Al	0.003%			*Contains no weld repair	
Carbon Eq A529	0.40%			*Contains no Mercury contamination	
Yield Strength test 1	54.6ksi			*Manufactured in accordance with the latest version	
Tensile Strength test 1	77.7ksi			of the plant quality manual	
Elongation test 1	27%			*Meets the "Buy America" requirements of 23 CFR6.	35.410, 49 CFR 661
Elongation Gage Lgth test 1	8IN			*Warning: This product can expose you to chemical	ls which are
Yield Strength test 2	60.2ksi			known to the State of California to cause cancer, b	pirth defects
Tensile Strength test 2	83.0ksi			or other reproductive harm. For more information g	0
				to www.P65Warnings.ca.gov	

0

REMARKS: