

1 STEEL MILL DRIVE **CMC STEEL TEXAS**

CERTIFIED MILL TEST REPORT

are accurate and conform to the reported grade specification We hereby certify that the test results presented here

Rolando A Davila 9

Quality Assurance Manager

1SERIES-BPS

Cert. No.: 85181133 / 080985A682

0

3376258509

DLVRY PCS / HEAT: 20 EA

DLVRY LBS / HEAT: 5120.000 LB

CUST PO#: 236439-11

BOL#: 74998553 Delivery#: 85181133

CUST P/N:

MELT DATE: 07/03/2022 ROLL DATE: 09/30/2022 GRADE: ASTM A36-19/A529-14 Gr 50 SECTION: ANG 4 X 4x1/2 20'0" A36/52950 HEAT NO.:1080985 **SEGUIN TX 78155-7510** O F US 70663-5424 Sulphur LA

318 N Cities Service Hwy 3376252300 Superior Supply & Steel Co For additional copies call 800-227-6489 0 -7 8002529017 US 70560-0781 New Iberia LA 217 Darnall Rd Superior Steel

Tensile Strength test 1 77			Carbon Eq A529 0.3			Ti 0.0	В 0.0	Sn 0.0			Mo 0.		Cr 0.	Cu 0.	Si 0.	s 0.	P 0.	Mn 0.	C 0.	Characteristic V
77.3ksi	54.3ksi		0.37%	0.34%	0.0099%	0.001%	0.0003%	0.011%	0.012%	0.003%	0.032%	0.11% Y		0.34%	0.18%	0.015%	0.013% Y	0.71% Eloi	0.15%	Value
												Yield to tensile ratio test2 0.70	Elongation Gage Lgth test 2 8IN				Yield to tensile ratio test1 0.70	Elongation Gage Lgth test 1 8IN	Elongation test 1 24%	Characteristic Value
or other reproductive harm. For more information go to www.P65Warnings.ca.gov	known to the State of California to cause cancer, birth defects	*Warning: This product can expose you to chemicals which are	*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661	of the plant quality manual	*Manufactured in accordance with the latest version	*Contains no Mercury contamination	*Contains no weld repair	*EN10204:2004 3.1 compliant	*100% melted, rolled, and manufactured in the USA	*Material is fully killed and is Hot Rolled Steel	The Following is true of the material represented by this MTR:	0		8	77.8ksi	54.8ksi	0		%	Characteristic Value

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W