

CMC STEEL TEXAS 1 STEEL MILL DRIVE SEGUIN TX 78155-7510

CERTIFIED MILL TEST REPORT

For additional copies call 800-227-6489

We hereby certify that the test results presented here are accurate and conform to the reported grade specification

Rolando A Davila

Н

0

1SERIES-BPS®

HEAT NO.:3118617

SECTION: FLAT 1/4X6 20'0" A36/52955 GRADE: ASTM A36-19/A529-14 Gr 55

ROLL DATE: 10/08/2022 MELT DATE: 09/25/2022

Cert. No.: 85217173 / 118617A088

S	Superior Supply & Steel Co
0	
L	Superior Supply & Steel Co 318 N Cities Service Hwy Sulphur LA
D	Sulphur LA

US 70663-5424 T 3376252300 O 3376258509 Superior Supply & Steel

318 City Service Highway

Sulphur LA US 70663-0000 3376252300

3376258509

Delivery#: 85217173 BOL#: 75055132

CUST PO#: P0237188-01

CUST P/N:

Quality Assurance Manager

DLVRY LBS / HEAT: 4896.000 LB

DLVRY PCS / HEAT: 48 EA

Characteristic	Value	Characteristic	Value	Characteristic Value
С	0.11%	Elongation Gage Lgth test 1	8IN	
Mn	0.80%	Yield to tensile ratio test1	0.80	
P	0.011%	Yield Strength test 2	63.8ksi	
S	0.040%	Tensile Strength test 2	79.9ksi	
Si	0.20%	Elongation test 2	29%	
Cu	0.37%	Elongation Gage Lgth test 2	8IN	
Cr	0.13%	Yield to tensile ratio test2	0.80	
Ni	0.17%			
Мо	0.052%			The Following is true of the material represented by this MTR:
V	0.015%			*Material is fully killed and is Hot Rolled Steel
Cb	0.017%			*100% melted, rolled, and manufactured in the USA
Sn	0.014%			*EN10204:2004 3.1 compliant
В	0.0003%			*Contains no weld repair
Ti	0.001%			*Contains no Mercury contamination
N	0.0142%			*Manufactured in accordance with the latest version
Carbon Eq A6	0.32%			of the plant quality manual
Carbon Eq A529	0.36%			*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 66
Yield Strength test 1	63.5ksi			*Warning: This product can expose you to chemicals which are
Tensile Strength test 1	79.7ksi			known to the State of California to cause cancer, birth defects
Elongation test 1	27%			or other reproductive harm. For more information go
				to www.P65Warnings.ca.gov

REMARKS: ALSO MEETS ASTM GRADE A36, A529-50, A529-55, A572-50, A572-55, A709-36, A709-50, AASHTO M270-36, M270-50, CSA G40.21-04 44W,50W, 55W