

CMC STEEL TEXAS

1 STEEL MILL DRIVE **SEGUIN TX 78155-7510**

CERTIFIED MILL TEST REPORT

For additional copies call 800-227-6489

are accurate and conform to the reported grade specification We hereby certify that the test results presented here

Rolando A Davila

1SERIES-BPS®

Cert. No.: 85206029 / 117512A111	GRADE: ASIM A36-19/A529-14 Gr 50 ROLL DATE: 09/14/2022 MELT DATE: 08/12/2022	SECTION: ANG 2 X 2x3/16 20'0" A36/52950	HEAT NO.:3117512
0	- 0	г о	S
0 3376258509	D Sulphur LA US 70663-5424 T 3376252300	O 318 N Cities Service Hwy	S Superior Supply & Steel Co
0	- T	- = (<u>^</u>
0 3376258509	P Sulphur LA US 70663-0000	H 318 City Service Highway	
DEVKY PCS / HEAT: 192 EA	CUST P/N: DLVRY LBS / HEAT: 9370.000 LB	BOL#: 75036604 CUST PO#: 236924-11	Quality Assurance Manager

Characteristic	Value	Characteristic Value	Characteristic Value
C	0.10%	Tensile Strength test 2 76.7ksi	
Mn	1.01%		
סי	0.012%		
s	0.038%		
S:	0.23%		
ည	0.28%		
ਨ	0.09%		
Z;	0.10%		
Мо	0.030%		The Following is true of the material represented by this MTR-
<	0.000%		*Material is fully killed and is Hot Rolled Steel
СЪ	0.012%		*100% melted, rolled, and manufactured in the USA
Sn	0.011%		*EN10204:2004 3.1 compliant
A	0.000%		*Contains no weld repair
Carbon Eq A529	0.36%		*Contains no Mercury contamination
			*Manufactured in accordance with the latest version
Yield Strength test 1	56.3ksi		of the plant quality manual
Tensile Strength test 1	77.1ksi		*Meets the "Buy America" requirements of 23 CFR635, 410, 49 CFR 661
Elongation test 1	27%		*Warning: This product can expose you to chemicals which are
Elongation Gage Lgth test 1	NIS		known to the State of California to cause cancer, birth defects
Yield Strength test 2	56.5ksi		or other reproductive harm. For more information go
			to the second of

REMARKS: ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W