

SEGUIN TX 78155-7510 1 STEEL MILL DRIVE **CMC STEEL TEXAS**

CERTIFIED MILL TEST REPORT

For additional copies call 800-227-6489

are accurate and conform to the reported grade specification We hereby certify that the test results presented here

1SERIES-BPS®

	0 3376258509		0 3376258509	
DLVRY PCS / HEAT: 132 EA	T 3376252300		T 3376252300	Cert. No.: 85310017 / 120655A934
DLVRY LBS / HEAT: 8976.000 LB	US 70663-5424	US 70663-5424	US 706	MELI DATE: 12/30/2022
CUST P/N:	P SULPHUR LA		D SULPHUR LA	RULL DATE: 01/19/2023
CUST PO#: P0239142-01	318 N CITIES SERVICE HWY	L 318 N CITIES SERVICE HWY	L 318 N C	GRADE: ASTM A36-19/A529-19 GR 50
BOL#: 75193665		I	0	SECTION: FLAT 1/4x4 20'0" A36/52950
Delivery#: 85310017	S Superior Supply & Steel Co	S Superior Supply & Steel Co S	S Superio	HEAT NO.:3120655

	i	\	Rolando A Davila
		Quality Assurance Manager	ice Manager
Superior Supply & Steel Co	S	S Superior Supply & Steel Co	Delivery#: 85310017
	Ξ		BOL#: 75193665
318 N CITIES SERVICE HWY	-	318 N CITIES SERVICE HWY	CUST PO#: P0239142-01
SULPHUR LA	7	SULPHUR LA	CUST P/N:
US 70663-5424		US 70663-5424	DLVRY LBS / HEAT: 8976.000
3376252300	7	3376252300	DLVRY PCS / HEAT: 132 EA

Charactariatio	W-1		
Characteristic	Value	Characteristic Value	Characteristic Value
c	0.12%	Yield Strength test 2 5	56.5ksi
Mn	0.99%		78.6ksi
۵	0.011%		31%
s	0.027%		
Si	0.21%		
Cu Cu	0.29%		
Cr	0.10%		
Z.	0.12%		
Mo	0.058%		The Following is true of the material represented by this MTR:
<	0.000%		*Material is fully killed and is Hot Rolled Steel
Сь	0.015%		*100% melted, rolled, and manufactured in the USA
Sn	0.016%		*EN10204:2004 3.1 compliant
AI	0.000%		*Contains no weld repair
Carbon Eq F1554	0.31%		*Contains no Mercury contamination
Carbon Eq A529	0.38%		*Manufactured in accordance with the latest version
			of the plant quality manual
Yield Strength test 1	56.4ksi		*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661
Tensile Strength test 1	78.3ksi		*Warning: This product can expose you to chemicals which are
Elongation test 1	26%		known to the State of California to cause cancer, birth defects
Elongation Gage Lgth test 1	NI8		or other reproductive harm. For more information go
	l		to www P65Warnings on any

REMARKS : ALSO MEETS ASTM GRADE A36, A52950, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W