

CMC STEEL TEXAS 1 STEEL MILL DRIVE **SEGUIN TX 78155-7510**

CERTIFIED MILL TEST REPORT

For additional copies call 800-227-6489

We hereby certify that the test results presented here are accurate and conform to the reported grade specification

Rolando A Davila

1SERIES-BPS ®

HEAT NO.:3118991 SECTION: ANG 3 X 3x3/8 20'0" A36/52950

GRADE: ASTM A36-19/A529-14 Gr 50

ROLL DATE: 10/18/2022 MELT DATE: 10/09/2022

Cert. No.: 85217173 / 118991A898

| S | Superior Supply & Steel Co |
|---|----------------------------|
| 0 | |
| L | 318 N Cities Service Hwy |

Sulphur LA US 70663-5424 3376252300 Т 0 3376258509

Superior Supply & Steel Н

318 City Service Highway Sulphur LA US 70663-0000

3376252300 0 3376258509 Delivery#: 85217173 BOL#: 75055132

CUST PO#: P0237188-01

CUST P/N:

Quality Assurance Manager

DLVRY LBS / HEAT: 4608.000 LB

DLVRY PCS / HEAT: 32 EA

| Characteristic | Value | Characteristic | Value | Characteristic Value |
|------------------------------|---------|------------------------------|---------|--|
| С | 0.10% | Yield Strength test 2 | 55.6ksi | |
| Mn | 1.06% | Tensile Strength test 2 | 74.9ksi | |
| Р | 0.012% | Elongation test 2 | 35% | |
| S | 0.038% | Elongation Gage Lgth test 2 | 8IN | |
| Si | 0.21% | Yield to tensile ratio test2 | 0.74 | |
| Cu | 0.35% | | | |
| Cr | 0.11% | | | |
| Ni | 0.11% | | | |
| Мо | 0.034% | | | The Following is true of the material represented by this MTR: |
| V | 0.000% | | | *Material is fully killed and is Hot Rolled Steel |
| Cb | 0.012% | | | *100% melted, rolled, and manufactured in the USA |
| Sn | 0.014% | | | *EN10204:2004 3.1 compliant |
| Al | 0.001% | | | *Contains no weld repair |
| Carbon Eq A529 | 0.37% | | | *Contains no Mercury contamination |
| Carbon Eq A992 | 0.34% | | | *Manufactured in accordance with the latest version |
| Yield Strength test 1 | 54.7ksi | | | of the plant quality manual |
| Tensile Strength test 1 | 73.7ksi | | | *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 662 |
| Elongation test 1 | 34% | | | *Warning: This product can expose you to chemicals which are |
| Elongation Gage Lgth test 1 | 8IN | | | known to the State of California to cause cancer, birth defects |
| Yield to tensile ratio test1 | 0.74 | | | or other reproductive harm. For more information go |
| 11110 10 10110110 10110 | | | | to www.P65Warnings.ca.gov |

REMARKS: ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W