

REF.B/L: 81158954  
 Date: 06/13/2023  
 Customer: 1592



Atlas Tube Corp. Kansas City  
 Burlington St  
 North Kansas City Missouri USA  
 64116  
 Tel:  
 Fax:

**MATERIAL TEST REPORT**

Shipped To  
 Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

Sold To  
 Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Material:** 3.0x3.0x250x20'0"(5x5)OTS  
**Material No:** 30030250  
**Purchase Order:** P0242031-01  
**Material No:** 40040375

**Sales Order:** 1922425  
**Heat No:** 22176382  
**Bundle No:** 5000028374  
**Heat:** 22176382  
**Material Note:** 22176382  
**Sales Or. Note:** 22176382

C	0.060	Mn	0.810	P	0.014	S	0.001	Si	0.030	Al	0.036	Cu	0.070	Cb	0.002	Mo	0.009	Ni	0.030	Cr	0.040	V	0.003	Ti	0.001	B	0.0001	N	0.0072	Ca	0.0025
<b>PCs</b>		<b>Yield</b>		<b>Tensile</b>		<b>Eln.2in</b>		<b>Method</b>		<b>Recycled Content</b>		<b>Post Consumer</b>		<b>Pre-Consumer</b>		<b>Post Industrial</b>		<b>% Harvested</b>		<b>Within Miles of Location</b>											
25		066200 Psi		071400 Psi		29 %		EAF		76.00%		95.00%		5.00 %		75%		500		USA											

**CE: 0.22**

**Certification**  
 ASTM A500-21 GRADE B&C

**Material:** 4.0x4.0x375x20'0"(3x3)REC  
**Sales Order:** 1920522  
**Heat No:** 23056742  
**Bundle No:** Z200002378  
**Heat:** 23056742  
**Material Note:** 23056742  
**Sales Or. Note:** 23056742

C	0.060	Mn	0.870	P	0.010	S	0.002	Si	0.020	Al	0.030	Cu	0.090	Cb	0.000	Mo	0.010	Ni	0.040	Cr	0.060	V	0.003	Ti	0.000	B	0.0001	N	0.0075	Ca	0.0000
<b>PCs</b>		<b>Yield</b>		<b>Tensile</b>		<b>Eln.2in</b>		<b>Method</b>		<b>Recycled Content</b>		<b>Post Consumer</b>		<b>Pre-Consumer</b>		<b>Post Industrial</b>		<b>% Harvested</b>		<b>Within Miles of Location</b>											
9		067700 Psi		072100 Psi		30 %		EAF		76.00%		95.00%		5.00 %		75%		500		USA											

**CE: 0.23**

**Certification**  
 ASTM A500-21 GRADE B&C

Authorized by Quality Assurance  
*Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

