



Atlas Tube Alabama
171 Cleage Dr
Birmingham Alabama USA
35217
Tel:
Fax:

REF.B/L: 81170088
Date: 08/22/2023
Customer: 1592

MATERIAL TEST REPORT

Shipped To
Superior Supply and Steel
318 North Cities Service Hwy
SULPHUR LA 70663
USA

Sold To
Superior Supply and Steel
PO Box 2388
SULPHUR LA 70664
USA

Material: 2.0x2.0x250x20"0(6x6). **Material No:** 0200202502000-B **Made in:** USA
Sales Order: 1944126 **Purchase Order:** P0243508-01 **Melted and Poured in:** USA
Heat No: SN5036 **AI:** 0.035 **Cu:** 0.120 **Cb:** 0.000 **Cr:** 0.040 **Ni:** 0.030 **Mo:** 0.010 **Si:** 0.017 **S:** 0.003 **P:** 0.008 **Mn:** 0.380 **C:** 0.200 **Ti:** 0.000 **B:** 0.0000 **N:** 0.0050 **Ca:** 0.0010
Bundle No: MC00215294 **PCs:** 36 **Yield:** 064252 Psi **Tensile:** 070702 Psi **Eln.2in:** 28.6% **Certification:** ASTM A500-21 GRADE B&C
Heat: SN5036 **MILL:** NUCOR **Mill Location:** Decatur,AL **Method:** EAF **Recycled Content:** 53.70% **Post Consumer:** 23.80% **Pre-Consumer (Post Industrial):** 29.90% **% Harvested:** 86% **Within Miles of Location:** 500
Material Note:
Sales Or. Note:

Material: 2.0x2.0x250x20"0(6x6). **Material No:** 0200202502000-B **Made in:** USA
Sales Order: 1944126 **Purchase Order:** P0243508-01 **Melted and Poured in:** USA
Heat No: SN5036 **AI:** 0.035 **Cu:** 0.120 **Cb:** 0.000 **Cr:** 0.040 **Ni:** 0.030 **Mo:** 0.010 **Si:** 0.017 **S:** 0.003 **P:** 0.008 **Mn:** 0.380 **C:** 0.200 **Ti:** 0.000 **B:** 0.0000 **N:** 0.0050 **Ca:** 0.0010
Bundle No: MC00215293 **PCs:** 36 **Yield:** 064252 Psi **Tensile:** 070702 Psi **Eln.2in:** 28.6% **Certification:** ASTM A500-21 GRADE B&C
Heat: SN5036 **MILL:** NUCOR **Mill Location:** Decatur,AL **Method:** EAF **Recycled Content:** 53.70% **Post Consumer:** 23.80% **Pre-Consumer (Post Industrial):** 29.90% **% Harvested:** 86% **Within Miles of Location:** 500
Material Note:
Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

