

Mill Certification

11/16/2023

MTR#:1532759-9 Lot #:110005276320 8812 HWY 79 W Jewett, TX 75846 US

903 626-4461 Fax: 903 626-6290

Melting Date: 10/28/2023

Sold To: SUPERIOR SUPPLY & STEEL

PO BOX 2388

SULPHUR, LA 70664 US

Ship To: SUI

SUPERIOR SUPPLY 318 CITIES SERVICE HWY

HWY-108

SULPHUR, LA 70663 US

Customer PO	P0245527-01	Sales Order #	11066701 - 1.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3016270
Grade	A36/A529 Gr 50, CSA 44W/50W	Lot #	110005276320
Size	0.25" x 1"	Heat #	1100052763
BOL#	BOL-1579525	Load #	1532759
Description	Hot Roll - Merchant Bar Quality Flat 1/4" x 1" A36/A529 Gr 50, CSA 44W/50W 20' 0" [240"] 2001-6000 lbs	Customer Part #	
Production Date	10/30/2023	Oty Shipped LBS	4902
Product Country Of Origin	United States	Qty Shipped EA	288
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	Cr (%)	Mo (%)	Cu (%)	<u>V (%)</u>	Nb (%)
0.13	0.85	0.017	0.022	0.209	0.10	0.16	0.03	0.26	0.023	0.002

Reduction Ratio 155.89:1

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	54800	70700	20.0
(2)	55200	71100	22.0

Comments:

MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/A529-05 GR50(345); A572/572M-07 GR50(345); A709/A709M-10 GR36(250); CSA G40.21-04 GR44W(300W)&GR50W(350W); AASHTO M270/270M-10 GR36(270); ASME SA36/SA36M-10; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

- 1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
- 2. Mercury not intentionally added at any point during manufacturing or testing of this material.
- 3. Welding or weld repair was not performed on this material.
- 4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
- Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.