



CMC STEEL ALABAMA
101 S 50TH STREET
BIRMINGHAM AL 35212-3525

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-6489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

1 SERIES-BPS[®]

Marcus W. McCluney - CMC Steel AL
Quality Assurance Manager

HEAT NO.: 1088501	S	Superior Supply & Steel Co	S	Superior Supply & Steel Co	Delivery#: 85630866
SECTION: FLAT 3/8X8 20'0" A36/52955	O		H		BOL#: 75698690
GRADE: ASTM A36-19/A529-19 Gr 55	L	318 N CITIES SERVICE HWY	I	318 N CITIES SERVICE HWY	CUST PO#: P0245785-01
ROLL DATE: 09/14/2023	D	SULPHUR LA	P	SULPHUR LA	CUST P/N:
MELT DATE: 09/02/2023	T	US 70663-5424	T	US 70663-5424	DLVRY LBS / HEAT: 4488,000 LB
Cert. No.: 85630866 / 088501B104	O	3376252300	O	3376258509	DLVRY PCS / HEAT: 22 EA
	O	3376258509			

Characteristic	Value	Characteristic	Value	Characteristic	Value
C	0.13%	Elongation test 1	25%	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov	
Mn	0.65%	Elongation Gage Lgth test 1	8IN		
P	0.016%	Yield to tensile ratio test1	0.74		
S	0.024%	Yield Strength test 2	55.9ksi		
Si	0.17%	Tensile Strength test 2	75.8ksi		
Cu	0.34%	Elongation test 2	26%		
Cr	0.21%	Elongation Gage Lgth test 2	8IN		
Ni	0.13%	Yield to tensile ratio test2	0.74		
Mo	0.037%				
V	0.003%				
Cb	0.012%				
Sn	0.010%				
B	0.0003%				
Ti	0.001%				
N	0.0076%				
Carbon Eq A6	0.32%				
Carbon Eq A529	0.35%				
Yield Strength test 1	55.9ksi				
Tensile Strength test 1	75.3ksi				

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A529-55, A572-50, A572-55, A709-36, A709-50, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W, 55W
ASME SA-36 2008A ADDEND A