

Mill Certification

12/12/2023

MTR#:1551234-9 Lot #:110004954860 8812 HWY 79 W Jewett, TX 75846 US 903 626-4461

Fax: 903 626-6290

Sold To: SUPERIOR SUPPLY & STEEL

PO BOX 2388

SULPHUR, LA 70664 US

Ship To: SUPERIOR SUPPLY

318 CITIES SERVICE HWY

HWY-108

SULPHUR, LA 70663 US

Customer PO	P0245378-01	Sales Order #	11066460 - 12.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3007430
Grade	Nucor Multigrade	Lot #	110004954860
Size	6" x 4" x 0.5"	Heat #	1100049548
BOL #	BOL-1597480	Load #	1551234
Description	Hot Roll - Merchant Bar Quality Unequal Angle 6" x 4" x 1/2" Nucor Multigrade 20' 0" [240"] 2001-6000 lbs	Customer Part #	
Production Date	08/04/2023	Oty Shipped LBS	4860
Product Country	United States	Qty Shipped EA	15
Of Origin Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements Melting Date: 07/23/2023

Melt Country of Origin: United States

ry of Origir	i : uniieo a	อเลเยร									
, , o. o. g									-1.46()	37.00()	NIII- (0/ \
C (%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	<u>Cr (%)</u>	<u>Mo (%)</u>	<u>Cu (%)</u>	11 (%)	<u>V (%)</u>	NO (76)
C 1/01	14111 1 797	- 1/4/							0.004	0.040	0.001
0.14	0.88	0.019	0.016	0.226	0.10	0.21	0.03	0.28	0.001	0.040	0.001
V. 1 T	0.00	0.0.0									

Sn (%) 0.010

ASTM A529 S78.2 CE (%): 0.40

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	53800	70100	22.0
(2)	53400	70300	23.0

Comments:

NUCOR MULTIGRADE MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/529M-05(2009) GR50(345); A572/572M-07 GR50(345); A709/709M-10 GR36(250) & GR50(345); CSA G40.21-04 GR44W(300W)& GR50W(350W); AASHTO M270/M270M-10 GR36(270) & GR50(345); ASME SA36/SA36M-07; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

- 1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
- 2. Mercury not intentionally added at any point during manufacturing or testing of this material.
- 3. Welding or weld repair was not performed on this material.
- 4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor
- 5. Results reported ASTM E45 (inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.