GÐ	GERDAU

CUSTOMER PURCHASE ORDER NUMBER

CA-ML-WHITBY 1 GERDAU CT WHITBY, ON LIN 5T1 Canada

EG00007577

Page 1 / 1 CERTIFIED MATERIAL TEST REPORT DOCUMENT ID: SHAPE / SIZE GRADE CUSTOMER BILL TO CUSTOMER SHIP TO 0000352735 Angle / 6X3 1/2X3/8 **GGMULTI** HEAT / BATCH WEIGHT LENGTH MANHATTAN,KS 66505-1688 LONGVIEW,TX 75604-4817 52110392/06 6,084 LB 20'00" USA USA SPECIFICATION / DATE or REVISION CUSTOMER MATERIAL Nº SALES ORDER ASTM A529-14, A572-15 000000506003161220 13517276/000010 ASTM A6-17,A36-14, ASME \$A-36 ASTM A709-18, AASHTO M270-15 DATE BILL OF LADING CSA G40.20-13/G40.21-13 11/10/2023 1302-0000166678

CHEMICAL COMPOSITION C (%) Mn (%) 0.13 1.00	P (%) S (%) 0.013 0.018	Si (%) Cu (%) 0.19 0.29	Ni (%) Cr (%) 0.10 0.11		Nb (%) CEgvA6 (%) 0.002 0.36	Sn (%) 0.011
MECHANICAL PROPERTIES Elong. (%) 22.50 22.50	G/L (Inches) 8.000 8.000	UTS (PSI) 73100 75200	UTS (MPa) 504 518	YS 0.2% (PSI) 55900 57400	YS (MPa) 385 396	

COMMENTS / NOTES

This grade meets the requirements for the following grades: ASTM Grades: A36; A529-50; A572-50; A709-36; A709-50 CSA Grades: 44W; 50W AASHTO Grades: M270-36; M270-50 ASME Grades: SA36

Gerdau's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling, or contact metalsrecycling@gerdau.com.

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdau possession. For all products other than billets, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, and Hot Rolled) in Canada. For billets, this material was produced (Electric Arc Furnace, Melted, and Continuously Cast) in Canada. CMTR complies with EN 10204 3.1.

Mackey BHASKAR YALAMANCHILI QUALITY DIRECTOR

Phone: (409) 267-1071 Email: Bhaskar. Yalamanchili@gerdau.com

Phone: (905) 668-8811 EXT 4055 Email: Leonardo, Nunes@gerdau.com