NUCOR

Mill Certification

11/16/2023

MTR#:1532759-9 Lot #:110005312760 8812 HWY 79 W Jewett, TX 75846 US 903 626-4461

Fax: 903 626-6290

Sold To: SUPERIOR SUPPLY & STEEL

PO BOX 2388

SULPHUR, LA 70664 US

Ship To: SUPERIOR SUPPLY 318 CITIES SERVICE HWY

HWY-108

SULPHUR, LA 70663 US

Customer PO	P0245527-01	Sales Order #	11066701 - 7.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3006108
Grade	Nucor Multigrade	Lot #	110005312760
Size	3" x 3" x 0.375"	Heat #	1100053127
BOL#	BOL-1579525	Load #	1532759
Description	Hot Roll - Merchant Bar Quality Equal Angle 3" x 3" x 3/8" Nucor Multigrade 20' 0" [240"] 4001-8000 lbs	Customer Part #	
Production Date	11/16/2023	Qty Shipped LBS	5040
Product Country Of Origin	United States	Oty Shipped EA	35
Original Item Description		Original Item Number	

Melt Country of Origin: United States						Melting Date: 11/10/2023					
C_(%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	<u>Сг (%)</u>	Mo (%)	Cu (%)	Ti (%)	V (%)	Nb (%)
0.12	0.88	0.018	0.016	0.203	0.11	0.20	0.03	0.27	0.001	0.039	0.001
<u>Sn (%)</u>											
0.009											

ASTM A529 S78.2 CE (%): 0.38

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in
(1)	55800	73200	8" (%) 20.0
(2)	57100	74200	25.0

Comments:

NUCOR MULTIGRADE MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/529M-19 GR50(345); A572/572M-18 GR50(345); A709/709M-10 GR36(250) & GR50(345); CSA G40.21-04 GR44W(300W)& GR50W(350W); AASHTO M270/M270M-10 GR36(270) & GR50(345); ASME SA36/SA36M-07; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

- 1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
- 2. Mercury not intentionally added at any point during manufacturing or testing of this material.
- 3. Welding or weld repair was not performed on this material.
- 4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
- 5. Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.