

SEGUIN TX 78155-7510 1 STEEL MILL DRIVE CMC STEEL TEXAS

CERTIFIED MILL TEST REPORT For additional copies call

800-227-6489

are accurate and conform to the reported grade specification We hereby certify that the test results presented here

Drew M Fischer

1SERIES-BPS®

US 70663-5424 T 3376252300 O 3376258509
1

to www.P65Warnings.ca.gov			
or other reproductive harm. For more information go		1 8IN	Elongation Gage Lgth test 1
known to the State of California to cause cancer, birth defects		1 31%	Elongation test 1
*Warning: This product can expose you to chemicals which are		1 76.0ksi	Tensile Strength test 1
*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661		1 58.3ksi	Yield Strength test 1
of the plant quality manual			
*Manufactured in accordance with the latest version		2 0.33%	Carbon Eq A992
*Contains no Mercury contamination		9 0.36%	Carbon Eq A529
*Contains no weld repair		AI 0.001%	A
*EN10204:2004 3.1 compliant		in 0.010%	Sn
*100% melted, rolled, and manufactured in the USA		. b 0.012%	СЬ
*Material is fully killed and is Hot Rolled Steel		V 0.000%	<
The Following is true of the material represented by this MTR:		10 0.034%	Мо
		Ni 0.11%	7
		Cr 0.09%	C
	Yield to tensile ratio test2 0.77	Cu 0.31%	C
	Elongation Gage Lgth test 2 8IN	Si 0.17%	
	Elongation test 2 30%		
	Tensile Strength test 2 76.1ksi	P 0.010%	
	Yield Strength test 2 58.4ksi	Mn 0.96%	8
	Yield to tensile ratio test1 0.77		
Characteristic Value	Characteristic Value	tic Value	Characteristic

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W