

Mill Certification

01/04/2024

MTR#:1559060-9 Lot #:110005292960 8812 HWY 79 W Jewett, TX 75846 US 903 626-4461

Fax: 903 626-6290

Melting Date: 11/02/2023

Sold To: SUPERIOR SUPPLY & STEEL Ship To: SUPERIOR

PO BOX 2388

SULPHUR, LA 70664 US

Ship To: SUPERIOR SUPPLY 318 CITIES SERVICE HWY

HWY-108

SULPHUR, LA 70663 US

Customer PO	P0246198-01	Sales Order #	11067808 - 4.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3006306
Grade	Nucor Multigrade	Lot #	110005292960
Size	4" x 4" x 0.25"	Heat #	1100052929
BOL#	BOL-1612260	Load #	1559060
Description	Hot Roll - Merchant Bar Quality Equal Angle 4" x 4" x 1/4" Nucor Multigrade 20' 0" [240"] 2001-6000 lbs	Customer Part #	
Production Date	11/08/2023	Qty Shipped LBS	5016
Product Country Of Origin	United States	Qty Shipped EA	38
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

_												
	<u>C (%)</u>	<u>Mn (%)</u>	<u>P (%)</u>	<u>S (%)</u>	Si (%)	<u>Ni (%)</u>	Cr (%)	<u>Mo (%)</u>	<u>Cu (%)</u>	<u>Ti (%)</u>	<u>V (%)</u>	<u>Nb (%)</u>
	0.13	0.89	0.021	0.011	0.210	0.13	0.28	0.03	0.31	0.001	0.040	0.001

Sn (%) 0.010

ASTM A529 S78.2 CE (%): 0.41

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in
			8" (%)
(1)	59900	74600	22.0
(2)	59300	74300	22.0

Comments:

NUCOR MULTIGRADE MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/529M-05(2009) GR50(345); A572/572M-07 GR50(345); A709/709M-10 GR36(250) & GR50(345); CSA G40.21-04 GR44W(300W)& GR50W(350W); AASHTO M270/M270M-10 GR36(270) & GR50(345); ASME SA36/SA36M-07; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

- 1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
- 2. Mercury not intentionally added at any point during manufacturing or testing of this material.
- 3. Welding or weld repair was not performed on this material.
- 4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
- 5. Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.