

CMC STEEL TEXAS
1 STEEL MILL DRIVE
SEGUIN TX 78155-7510

S

0

L

D

0

3376258509

CERTIFIED MILL TEST REPORT

For additional copies call 800-227-6489

We hereby certify that the test results presented here are accurate and conform to the reported grade specification

Shew Lische

Drew M Fischer

1SERIES-BPS®

HEAT NO.:3124255 SECTION: FLAT 1/2x1-1/2 20'0" A36/52950 GRADE: ASTM A36-19/A529-19 GR 50

ROLL DATE: 07/26/2023 MELT DATE: 07/22/2023

Cert. No.: 85664066 / 124255A294

Superior Supply & Steel Co
318 N CITIES SERVICE HWY
SULPHUR LA
US 70663-5424
3376252300

S Superior Supply & Steel Co H
I 318 N CITIES SERVICE HWY
P SULPHUR LA
US 70663-5424
T 3376252300
O 3376258509 Delivery#: 85664066 BOL#: 75752256

CUST PO#: P0246363-01

CUST P/N:

Quality Assurance Manager

DLVRY LBS / HEAT: 4590.000 LB

DLVRY PCS / HEAT: 90 EA

Characteristic	Value	Characteristic	Value	Characteristic Value
С	0.10%	Elongation Gage Lgth test 1	8IN	
Mn	1.04%	Yield to tensile ratio test1	0.74	
Р	0.006%	Yield Strength test 2	52.2ksi	
S	0.038%	Tensile Strength test 2	70.1ksi	
Si	0.18%	Elongation test 2	28%	
Cu	0.24%	Elongation Gage Lgth test 2	8IN	
Cr	0.05%	Yield to tensile ratio test2	0.74	
Ni	0.09%			
Мо	0.022%			The Following is true of the material represented by this MTR:
V	0.000%			*Material is fully killed and is Hot Rolled Steel
Cb	0.013%			*100% melted, rolled, and manufactured in the USA
Sn	0.007%			*EN10204:2004 3.1 compliant
Al	0.002%			*Contains no weld repair
Carbon Eq F1554	0.29%			*Contains no Mercury contamination
Carbon Eq A529	0.34%			*Manufactured in accordance with the latest version
Carbon Eq A992	0.31%			of the plant quality manual
-				*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661
Yield Strength test 1	52.9ksi			*Warning: This product can expose you to chemicals which are
Tensile Strength test 1	71.4ksi			known to the State of California to cause cancer, birth defects
Elongation test 1	28%			or other reproductive harm. For more information go
				to www.P65Warnings.ca.gov

REMARKS : ALSO MEETS ASTM GRADE A36, A529-50, A572-50, A709-36, A709-50, A992, AASHTO M270-36, M270-50, CSA G40.21-04 44W, 50W ALSO MEETS THE REQUIREMENTS OF ASME SA36