

Atlas Tube (U.S.) Inc.
 13101 Eckles Road
 Plymouth Michigan USA
 48170
 Tel: 313-454-5600
 Fax: 313-454-1474

Atlas Tube
 A DIVISION OF ZEKELMAN INDUSTRIES

REF./B/L: 81203624
 Date: 02/21/2024
 Customer: 1592

Sold To
 Superior Supply and Steel
 PO Box 2388
 SULPHUR LA 70664
 USA

MATERIAL TEST REPORT

Shipped To
 Superior Supply and Steel
 318 North Cities Service Hwy
 SULPHUR LA 70663
 USA

Material: 2.0x2.0x250x20*0*0(7x2)NL Material No: 20020250 Made in: USA
 Melted and Poured in: Canada

Sales Order: 1999380 Purchase Order: P0246536-01

Heat No: C Mn P S Si Al Cu Cb Mo Ni Cr V Ti B N Ca

713704 0.170 0.770 0.011 0.008 0.023 0.047 0.050 0.002 0.005 0.017 0.061 0.002 0.002 0.0002 0.0020 0.0002

Bundle No: M301402370 13 Yield: 061527 Psi Tensile: 071490 Psi Eln.2in: 25 % Certification: ASTM A500-21 GRADE B&C CE: 0.32

Heat: 713704 MILL STELCO Mill Location: Nanticoke,ON Method: BOF Recycled Content: 36.90% Post Consumer: 19.80% Pre-Consumer (Post Industrial): 14.40% % Harvested: 100% Within Miles of Location: 1000

Material Note: Material: 2.5x2.5x250x20*0*0(8x4)FR Material No: 25025250 Made in: USA
 Melted and Poured in: USA

Sales Order: 1999380 Purchase Order: P0246536-01

Heat No: C Mn P S Si Al Cu Cb Mo Ni Cr V Ti B N Ca

32348420 0.190 0.740 0.012 0.001 0.040 0.023 0.130 0.001 0.020 0.060 0.080 0.000 0.001 0.0002 0.0060 0.0020

Bundle No: M301423363 32 Yield: 067465 Psi Tensile: 078240 Psi Eln.2in: 25.3 % Certification: ASTM A500-13 GRD B&C CE: 0.35

Heat: 32348420 SIDI MILL Butter,IN Method: EAF Recycled Content: 89.00% Post Consumer: 80.00% Pre-Consumer (Post Industrial): 9.00% % Harvested: 99% Within Miles of Location: 500

Material Note: Sales Or. Note:

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

