

## CMC STEEL ARKANSAS 100 COLUMBIA 7-B MAGNOLIA AR 71753-9238

## CERTIFIED MILL TEST REPORT For additional copies call 800-227-6489

We hereby certify that the test results presented here are accurate and conform to the reported grade specification

Jimmy Glass

			Quality Assurance Manager
HEAT NO.:311/861 SECTION: ANG 1 1/2 X 1 1/2x3/16 20'0"	S Superior Supply & Steel Co	S Superior Supply & Steel	Delivery#: 85206029
A36/52950	L 318 N Cities Service Hwy	1 318 City Service Highway	BOL#: 75036604
GRADE: ASTM A36-19A529-14 GR 50	D Sulphur LA		CUST P/N:
MEIT DATE: 08/26/2022		US 70663-0000	DLVRY LBS / HEAT: 4680.000 LB
Cert. No.: 85206029 / 117861C117	T 3376252300 O 3376258509	T 3376252300 O 3376258509	DLVRY PCS / HEAT: 130 EA
Characteristic Value	Characteristic	Value	Characteristic Value
C 0.17%	- L	est 2 73 7ksi	Authoritions Ading
Mn 0.72%	Elongation test 2		
P 0.007%	Elongation		
S 0.027%			
Si 0.21%			
Cu 0.29%			
Cr 0.05%			
Ni 0.09%			
Mo 0.020%	<del>, , , , , , , , , , , , , , , , , , , </del>	The Fo	The Following is true of the material represented by this MTR:
V 0.000%		*Mat	*Material is fully killed and is Hot Rolled Steel
Cb 0.001%		*100	*100% melted, rolled, and manufactured in the USA
Sn 0.009%		*EN1C	*EN10204:2004 3.1 compliant
Al 0.001%		*Cont	*Contains no weld repair
Carbon Eq A529 0.36%		*Cont	*Contains no Mercury contamination
		manu.	*Manufactured in accordance with the latest version
		ofth	of the plant quality manual
		*Meei	*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661
		*Warr	*Warning: This product can expose you to chemicals which are
		knou	known to the State of California to cause cancer, birth defects
Yield Strength test 2 52.3ksi		oroti	or other reproductive harm. For more information go
		to ww	to www.P65Warnings.ca.gov