

Mill Certification

09/05/2024

MTR#:1762072-9 Lot #:110005935161 8812 HWY 79 W Jewett, TX 75846 US 903 626-4461 Fax: 903 626-6290

Sold To: SUPERIOR SUPPLY & STEEL PO BOX 2388 SULPHUR, LA 70664 US Ship To: SUPERIOR SUPPLY 217 DARNALL RD NEW IBERIA, LA 70560 US

Customer PO	P0251533-08	Sales Order #	11076959 - 2.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3017946
Grade	Nucor Multigrade	Lot #	110005935161
Size	0.75" x 12"	Heat #	1100059351
BOL #	BOL-1805014	Load #	1762072
Description	Hot Roll - Merchant Bar Quality UM Plate 3/4" x 12" Nucor Multigrade 20' 0" [240"] 2001-6000 lbs	Customer Part #	
Production Date	06/06/2024	Qty Shipped LBS	9800
Product Country Of Origin	United States	Qty Shipped EA	16
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

Melt Country of Origin : United States							Melting Date: 06/02/2024						
Roll Country of Origin : United States							Rolling Date: 06/06/2024						
	<u>C (%)</u>	<u>Mn (%)</u>	<u>P (%)</u>	<u>S (%)</u>	<u>Si (%)</u>	<u>Ni (%)</u>	<u>Cr (%)</u>	<u>Mo (%)</u>	<u>Cu (%)</u>	<u>Ti (%)</u>	<u>V (%)</u>	<u>Nb (%)</u>	
	0.14	0.88	0.010	0.034	0.190	0.10	0.12	0.03	0.21	0.000	0.062	0.002	
	- (

<u>Sn (%)</u> 0.008

ASTM A529 S78.2 CE (%): 0.38

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	56200	72100	25.0
(2)	56400	72300	22.0

Comments:

NUCOR MULTIGRADE MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/529M-05(2009) GR50(345); A572/572M-07 GR50(345); A709/709M-10 GR36(250) & GR50(345); CSA G40.21-04 GR44W(300W)& GR50W(350W); AASHTO M270/M270M-10 GR36(270) & GR50(345); ASME SA36/SA36M-07; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A

2. Mercury not intentionally added at any point during manufacturing or testing of this material.

3. Welding or weld repair was not performed on this material.

4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.

5. Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.