

Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81234260  
 Date: 07/24/2024  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

**Material:** 3.0x2.0x120x20'0"0(5x7). **Material No:** 300201202000 **Made in:** USA  
**Sales Order:** 2070527 **Purchase Order:** P0250336-01 **Melted and Poured in:** USA  
**Cust Material#:** 982024533

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
B406022	0.210	0.460	0.009	0.002	0.020	0.022	0.100	0.000	0.020	0.040	0.050	0.000	0.001	0.0001	0.0069	0.0019

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.31		
MC00237502	35	064850 Psi	074528 Psi	28.4 %	ASTM A500-23 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
B406022	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:  
 Sales Or. Note:

**Material:** 4.0x2.0x250x20'0"0(5x5). **Material No:** 400202502000 **Made in:** USA  
**Sales Order:** 2072839 **Purchase Order:** P0250336-01 **Melted and Poured in:** USA  
**Cust Material#:** 982024750

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
A407607	0.210	0.490	0.009	0.003	0.020	0.031	0.100	0.001	0.020	0.040	0.060	0.001	0.002	0.0001	0.0079	0.0018

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.32		
MA00188962	25	061721 Psi	080240 Psi	27.7 %	ASTM A500-23 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
A407607	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

Material Note:  
 Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act.

