

Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81223679  
 Date: 05/24/2024  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

**Material:** 1.5x1.5x065x20'0"0(8x8).A513      **Material No:** 0150150652000-A513      **Made in:** USA  
**Sales Order:** 2028518      **Purchase Order:** P0247701-01      **Melted and Poured in:** USA  
**Heat No:** A404569      **CE:** 0.15      **Cust Material#:** 982024167

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
A404569	0.060	0.330	0.015	0.002	0.030	0.026	0.120	0.001	0.020	0.050	0.070	0.000	0.002	0.0000	0.0063	0.0018

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE		
MC00236338	64	000000 Psi	000000 Psi	%	ASTM A513-20A, TYPE 1	0.15		
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
A404569	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

**Material Note:**  
**Sales Or. Note:**

**Material:** 2.0x2.0x250x20'0"0(6x6).      **Material No:** 0200202502000-B      **Made in:** USA  
**Sales Order:** 2050914      **Purchase Order:** P0249265-01      **Melted and Poured in:** USA  
**Heat No:** A404989      **CE:** 0.32      **Cust Material#:** 982024310

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
A404989	0.210	0.460	0.012	0.002	0.030	0.024	0.100	0.001	0.020	0.060	0.070	0.001	0.001	0.0001	0.0073	0.0020

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE		
MC00238041	36	073989 Psi	081235 Psi	25.1 %	ASTM A500-23 GRADE B&C	0.32		
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
A404989	SDI	Columbus,MS	EAF	76.00%	95.00%	5.00 %	75%	500

**Material Note:**  
**Sales Or. Note:**

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

