

SEGUIN TX 78155-7510 1 STEEL MILL DRIVE CMC STEEL TEXAS

CERTIFIED MILL TEST REPORT

For additional copies call 800-227-6489

> are accurate and conform to the reported grade specification We hereby certify that the test results presented here

Rolando A Davila

Quality Assurance Manager

1SERIES-BPS ®			Quality Assurance Manager
HEAT NO.:1080928	S	Superior Supply & Steel Co	D.II*. OF 10000
SECTION: ANG 3 X 3x3/8 20'0" A36/52950		Ι (BOL#: 74932400
GRADE: ASTM A36-19/A529-14 Gr 50	<u>υ</u>	318 N Cities Service Hwy	CUST PO#: 235088-11
ROLL DATE: 08/08/2022	DS	Sulphur LA P New Iberia LA	CUST P/N:
MELT DATE: 07/01/2022	US	5424 US 70560	
Cert. No.: 85136390 / 080928A898	3	3376252300 T 8002529017	
	0 3	3376258509	
Characteristic Value		Characteristic Value	Characteristic Value
C 0.16%		Elongation test 1 25%	
Mn 0.72%			
P 0.015%		Yield to tensile ratio test1 0.73	
S 0.018%			
Si 0.18%		Tensile Strength test 2 76.1ksi	
Cu 0.37%		Elongation test 2 27%	
Cr 0.17%		Elongation Gage Lgth test 2 8IN	
		Yield to tensile ratio test2 0.72	
Mo 0.036%			The Following is true of the material represented by this MTR:
V 0.004%			*Material is fully killed and is Hot Rolled Steel
Cb 0.009%			*100% melted, rolled, and manufactured in the USA
Sn 0.012%			*EN10204:2004 3.1 compliant
B 0.0002%			*Contains no weld repair
Ti 0.001%			*Contains no Mercury contamination
N 0.0100%			*Manufactured in accordance with the latest version
Carbon Eq A6 0.35%			of the plant quality manual
Carbon Eq A529 0.38%			*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661
			*Warning: This product can expose you to chemicals which are
Yield Strength test 1 54.7ksi			known to the State of California to cause cancer, birth defects
Tensile Strength test 1 75.4ksi			or other reproductive harm. For more information go
			to www.P65Warnings.ca.gov