SWVA, INC.
A Subsidiary of
STEEL OF WEST VIRGINIA
Phone (304)696-6529

PACKING LIST/MTR

CUSTOMER ORDER NO	DATED	OUR ORDER NO	FRIGHT PMT	CUSTOMER NO	CHANGE DATE
4500523859	1/27/22	57833 1	XXX & INCL	71960001	

DATE SHIPPED			LOAD NUMBER
2	08	22	2 2

ROUTE REQUESTED	TERMS
TRUCK	NET 30 DAYS

F.O.B WURTLAND

ROUTING VIA FLS B.O.L.# 566891

This is to certify that the material specification is a true and correct report as contained in the records of this company.

XXX

Nitalia Harris - Metallurgist

	PROD CODE	DESCRIPTION	LENGTH ORDERED	QUANTITY ORDERED	ESTIMATED WEIGHT	BUNDLES SHIPPED	QUANTITY THIS SHIPMENT PIECES	LIN FEET	POUNDS
	2680	4" X 7.7# STD I BEAM							
		NO HOLES, BARE							
		NO CLIPS							
		SWV 65 ASTM - ASTM A36-19/A572-18 GR50/A709-18 GR36&50							
		A36/A572 GR 50							
		TARP;TO SHIP ASAP!!!							
		CALL 800-874-5198 FOR APPOINTMENT							
		NOTE BUNDLES PER HEAT ON PAPERWORK							
		268020	20'	288 PCS	44,352#	12 of 24	288	20'	44,352
							TARP MATERIAL		

All melting and manufacturing processes for these materials occurred in the U.S.A.

HEATNO	Strength (P.S.I) Yield	Tensile	Elongation %	Lth	Cu	Cr	Ni	Mo	Nb
11366	58000	78000	21.4	8	.24	.16	.09	.03	.001
11255	51000	70000	22.8	8	.24	.16	.11	.04	.002
23411	55000	75000	22.8	8	.25	.16	.10	.03	.001
23405	52000	73000	21.6	8	.24	.13	.09	.03	.001
11360	54000	75000	23.2	8	.34	.17	.09	.03	.001
23408	53000	74000	22.5	8	.27	.15	.09	.02	.003
23410	50000	70000	21.5	8	.36	.15	.09	.03	.003

HEAT NO	C	MN	P	S	SI	V	SN	CE
11366	.16	.94	.025	.036	.28	.027	.011	.38
11255	.15	.70	.012	.032	.22	.027	.010	.34
23411	.15	.84	.018	.033	.25	.025	.009	.36
23405	.15	.79	.012	.024	.24	.025	.009	.34
11360	.14	.84	.019	.024	.30	.025	.020	.35
23408	.15	.78	.013	.027	.23	.025	.010	.35
23410	.21	.95	.022	.032	.23	.029	.010	.38