Date: 9/27/2022 To: SENTRY SUPPLY dba SO#: A732164 Ln#: 1 From:

PO#: P0236323-08 Part: A202003740* Qty: 16 Heat#: 1100036950* Tag: T01092722



Mill Certification 09/07/2022

MTR#:1126517-6 Lot #:110003695061 8812 HWY 79 W Jewett, TX 75846 US 903 626-4461 Fax: 903 626-6290

Customer PO	ssw127723	Sales Order #	11046320 - 4.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	1054383
Grade	A36/A529 Gr 50, CSA 44W/50W	Lot #	110003695061
Size	2" x 2" x 0.375"	Heat #	1100036950
BOL#	BOL-1228677	Load #	1126517
Description	Hot Roll - Merchant Bar Quality Equal Angle 2" x 2" x 3/8" A36/A529 Gr 50, CSA 44W/50W 40' 0" [480"] 10001-15000 ibs	Customer Part #	
Production Date	06/30/2022	Qty Shipped LBS	10152
Product Country Of Origin	United States	Qty Shipped EA	54
Original Item Description		Original Item Number	

Melt Country of Origi						-		N	felting Da	ite: 06/22/	2022		
C (%)	Mn (%)	P (%)	S (%)	SI (%)	NL (%)	Cr (%)	Mo (%)	Cu (%)	Y (%)	Nb (%)	•	•	
0.13	0.82	0.015	0.018	0.203	0.12	0.24	0.04	0.30	0.034	0.003			

Reduction Ratio 28.23:1

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)		
(1)	55000	73900	27.0		
(2)	54900	74000	26.0		

MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/A529-05 GR50(345); A572/572M-07 GR50(345); A709/A709M-10 GR36(250); CSA G40.21-04 GR44W(300W)&GR50W(350W); AASHTO M270/270M-10 GR36(270); ASME SA36/SA36M-10; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

- 1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
- 2. Mercury not intentionally added at any point during manufacturing or testing of this material.
- 3. Welding or weld repair was not performed on this material.

 4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
- 5. Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.