

SANMA FASTENER (ZHEJJANG) CO.,LTD

The report is issued according to EN 10204:2004 3.1 and ISO 16228 F3.1

地址:浙江省嘉兴市海盐县于城镇振兴路 313 号。

电话(Tel): 0573-86466128

NO.313 Zhenxing Road, Yucheng Town, Haiyan County.

(∮)∜(Fax): 0573-86466118

Jiaxing City, Zhejiang Province

12 / ([(1.1) | (1.1) | (1.1) |

| | | 期 Report Date:2021.12.27

Country of Origin: China

品 名 Product: ASTM A563-15 GRADE DH 数 量Quantity:14.40mpcs Heavy Hex Nuts 标 记 Marker: SHS DH 规格 Size: 5/8-11+0.020 检验标准 Inspection Standard: A563-15 GRADE DH 表面处理 Finish: HDG W/WAX ASTM F2329-15 尺寸标准 Dimensional Specification: ASME B18.2.2-2015

批号Lot No: N2021092118HHW、钢材性质 STEEL PROPERTIES:

材质 Material:SWRCH45K 热处理批号 Heat No:G190005388 规格 Steel Size:o24mm

ELEMENT (成份)	C%	Mn%	P%	S%	Si%	Cr%	Ni%
TEST Facility:S	0.44	0.63	0.014	0.006	0.22		

1、项目检测 Inspections Item:

检测项目	标 准 值	实 測 值	判定	
<u> Item</u>	Specified(in)	Actual Result	Judgment	
TEST Facility :M Appearance	Passed	Passed	OK	
TEST Facility :M Across Flat(in)	1.031-1.062	1.035-1.042	OK	
TEST Facility :M Across Corner(in)	1.175-1.227	1.184-1.192	OK	
TEST Facility :M Thickness(in)	0.587-0.631	0.595-0.620	OK	
TEST Facility :M	2B GO	OK	OK.	
Thread	2B NOGO	OK	OK	
TEST Facility :M			OK	
Hardness	24-35	30-33		
TEST Facility :M			OK	
Proof Load	175KSI	175KSI		
TEST Facility M		94-97	-OV	
Hardness After 24H AT 540 °C	MIN 89		()	
TEST Facility :M			STATE OF THE STATE	
Tempering Temperature	Min 455	530-545	700 JA	
TEST Facility :M		00 ID 0 (CD		
Macro Etch Test	\$1/R1/C1-S4/R4/C4	S2/R2/C2	Dien und	
TEST Facility :M			(本) 其 图	
Plating thickness	Min 50 μ m	55-60 μ m	UB	

MFG ISO9001 CERTIFICATE NO: 04308Q12140R0M

品保主管 Signature:

HU SHAO QING