

2

Page: 1 Document Name: untitled

H130 SMSTAN ARCELORMITTAL USA INC. 11/04/11
 N020 D126130 CHEMISTRY TEST RESULTS 16:31:46

*Action: Heat: 144928 Chg By: A1464042 Date Chg: 08/24/11
 Actual Spec: 566270000 Tap Date: 08/24/11 Sample Time 00.32.00 More:
 Supplier Name: WEST Heat: 2011-144928

C	0.16000	MN	0.77000	P	0.00900	S	0.01000	SI	0.01000
CU	< 0.00010	NI	< 0.00010	MO	0.01000	CR	0.02000	CB	0.00100
V	0.00100	AL	0.04300	AS		SN	0.00400	TI	0.00100
SA		N	0.00410	PB		TE		BI	
H		CA	< 0.00010	O		ZR		SB	0.00100
CE		LA		SE		MG		B	0.00010

Slabs(s)	Applied Spec	Slab(s)	Applied Spec
_____ to _____	_____	_____ to _____	_____
_____ to _____	_____	_____ to _____	_____
_____ to _____	_____	_____ to _____	_____
_____ to _____	_____	_____ to _____	_____
_____ to _____	_____	_____ to _____	_____
_____ to _____	_____	_____ to _____	_____

Command+====>

F1=HELP F3=EXIT F4=PROMPT F5=REFRESH F12=CANCEL

047761

Date: 11/4/2011 Time: 4:30:55 PM