



**CERTIFIED MATERIAL TEST REPORT**

US-ML-CARTERSVILLE  
 384 OLD GRASSDALE ROAD NE  
 CARTERSVILLE, GA 30121  
 USA

		GRADE GGMULTI	SHAPE / SIZE Misc Channel / 8 X 22.8#	DOCUMENT ID: 0000557617
		LENGTH 40'00"	WEIGHT 18,240 LB	HEAT / BATCH 55082762/02
SALES ORDER 12201606/000160		CUSTOMER MATERIAL N° 00000000268228040		SPECIFICATION / DATE or REVISION ASTM A529-14, A572-15 ASTM A6-17,A36-14, ASME SA-36 ASTM A709-18, AASHTO M270-15 CSA G40.20-13/G40.21-13
CUSTOMER PURCHASE ORDER NUMBER 4500536388	BILL OF LADING 1323-0000223125	DATE 11/20/2022		

CHEMICAL COMPOSITION													
C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Ni (%)	Cr (%)	Mo(%)	V (%)	Nb (%)	N (%)	CEqvA6 (%)	Sn (%)
0.07	0.90	0.015	0.032	0.23	0.30	0.11	0.13	0.034	0.001	0.020	0.0083	0.28	0.019

MECHANICAL PROPERTIES						
Elong. (%)	G/L (Inches)	UTS (PSI)	UTS (MPa)	YS 0.2% (PSI)	YS (MPa)	
24.40	8.000	71100	490	54600	377	
24.30	8.000	71300	492	53800	371	


**COMMENTS / NOTES**

This grade meets the requirements for the following grades:  
 ASTM Grades: A36; A529-50; A572-50; A709-36; A709-50  
 CSA Grades: 44W; 50W  
 AASHTO Grades: M270-36; M270-50  
 ASME Grades: SA36

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdau possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.

 **BHASKAR YALAMANCHILI**  
 QUALITY DIRECTOR

Phone: (409) 267-1071 Email: Bhaskar.Yalamanchili@gerdau.com

 **YAN WANG**  
 QUALITY ASSURANCE MGR.

Phone: (770) 387 5718 Email: yan.wang@gerdau.com