

Atlas Tube Arkansas  
 6651 E Hwy 137  
 Blytheville Arkansas USA  
 72315  
 Tel:  
 Fax:



REF.B/L: 81147374  
 Date: 04/12/2023  
 Customer: 179

MATERIAL TEST REPORT

Material: 5.0x5.0x250x48"0(4x2).

Material No: 500502504800

Made In: USA

Sales Order: 1900553

Purchase Order: C452006014

Melted and Poured In: USA  
 Cust Material#: 6550025048

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	TI	B	N	Ca
22163091	0.210	0.750	0.009	0.001	0.040	0.027	0.110	0.000	0.021	0.060	0.050	0.003	0.001	0.0002	0.0067	0.0018
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Tensile</b>	<b>Eln.2in</b>	<b>Certification</b>											
M400224138	8	063483 Psi	077819 Psi	37 %	ASTM A500-21 GRADE B&C											
Heat	MILL	Mill Location	Osceola,AR	Method	Recycled Content	Post Consumer	Pre-Consumer	(Post Industrial)	% Harvested	Within Miles of Location						
22163091	BIGRIVER	Osceola,AR	EAF	76.00%	95.00%	5.00 %	75%	500								

Material Note:

Material: 8.0x4.0x500x40"0(2x2).

Material No: 800405004000

Made In: USA

Sales Order: 1900072

Purchase Order: C452006011

Melted and Poured In: USA  
 Cust Material#: 6680040050040

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	TI	B	N	Ca
2131237	0.200	0.760	0.010	0.003	0.020	0.040	0.090	0.001	0.010	0.030	0.050	0.004	0.002	0.0000	0.0060	0.0020
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Tensile</b>	<b>Eln.2in</b>	<b>Certification</b>											
M500462397	4	063815 Psi	080109 Psi	35 %	ASTM A500-21 GRADE B&C											
Heat	MILL	Mill Location	HICKMAN,AR	Method	Recycled Content	Post Consumer	Pre-Consumer	(Post Industrial)	% Harvested	Within Miles of Location						
2131237	NUCOR	HICKMAN,AR	EAF	52.50%	31.80%	20.70%	74%	500								

Material Note:

Authorized by Quality Assurance: *Jason Richard*

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. This document is in compliance with the requirements of EN 10204 type 3.1

