

Atlas Tube Arkansas  
 6651 E Hwy 137  
 Blytheville Arkansas USA  
 72315  
 Tel:  
 Fax:



REF.B/L: 81144293  
 Date: 03/23/2023  
 Customer: 179

**MATERIAL TEST REPORT**

**Material:** 8.0x6.0x375x20'0(3x2). **Material No:** 800603752000 **Made in:** USA  
**Sales Order:** 1892185 **Purchase Order:** C452005962 **Melted and Poured in:** USA  
**Cust Material#:** 6680060037520

| Heat No | C     | Mn    | P     | S     | Si    | Al    | Cu    | Cb    | Mo    | Ni    | Cr    | V     | Ti    | B      | N      | Ca     |
|---------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|--------|--------|--------|
| 2130531 | 0.200 | 0.750 | 0.011 | 0.003 | 0.030 | 0.030 | 0.080 | 0.001 | 0.010 | 0.030 | 0.070 | 0.003 | 0.002 | 0.0000 | 0.0050 | 0.0010 |

| Bundle No  | PCs   | Yield         | Tensile    | EIn.2in          | Certification          | CE: 0.35                       |             |                          |
|------------|-------|---------------|------------|------------------|------------------------|--------------------------------|-------------|--------------------------|
| M500459797 | 6     | 069119 Psi    | 086193 Psi | 34 %             | ASTM A500-21 GRADE B&C |                                |             |                          |
| Heat       | MILL  | Mill Location | Method     | Recycled Content | Post Consumer          | Pre-Consumer (Post Industrial) | % Harvested | Within Miles of Location |
| 2130531    | NUCOR | HICKMAN,AR    | EAF        | 52.50%           | 31.80%                 | 20.70%                         | 74%         | 500                      |

Material Note:

Sales Or. Note:

Authorized by Quality Assurance: *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. This document is in compliance with the requirements of EN 10204 type 3.1

