
 <p>GERDAU US-ML-MIDLOTHIAN 300 WARD ROAD MIDLOTHIAN, TX 76065 USA</p>	GRADE A992/A572-50 Wide Flange Beam / 14 X 26# / 360 X 39.0		DOCUMENT ID: 0000851714
	LENGTH 40'00"	PCS 8	WEIGHT 8,320 LB
SALES ORDER 12403139/000010		SPECIFICATION / DATE OF REVISION ASTM A6-17 ASTM A709-18 ASTM A992-20, A572-21 CSA G40.21-13 345WM, 50W	
CUSTOMER PURCHASE ORDER NUMBER SSW131777		CUSTOMER MATERIAL N° DATE 11/07/2022	
BILL OF LADING 1327-0000499604			


CHEMICAL COMPOSITION		V (%)	Nb (%)	Al (%)	CEqvA6 (%)
C (%)	0.10	0.001	0.018	0.001	0.31
Mn (%)	0.89				
P (%)	0.007				
S (%)	0.028				
Si (%)	0.22				
Cu (%)	0.28				
Ni (%)	0.09				
Cr (%)	0.16				
Mo (%)	0.025				
Sn (%)	0.005				

MECHANICAL PROPERTIES		G/L (mm)	Elong. (%)
YS 0.2% (PSI)	59975	200.0	23.50
	60425	200.0	24.80
YS (MPa)	414		
	417		
UTS (MPa)	511		
	515		
UTS (PSI)	74162		
	74681		
Y/T ratio (%)	0.810		
	0.810		

COMMENTS / NOTES

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdaul possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.


 BHASKAR YALAMANCHILI
 QUALITY DIRECTOR


 WADE LUMPKINS
 QUALITY ASSURANCE MGR.