GERDAU			CERTIFIED MATERIAL TEST REPORT						GRADE A992/A572-50		13	SHAPE / SIZE Wide Flange Beam / 12 X 65# / 31 X 97		Page 1 / 1 DOCUMENT : 0 0000457930	
									LENGT 20'00"	H	PCS 4	WEIGHT 5,200 LB	HEAT / 6014501		
SS-ML-PETERSBURG 5801 HOFHEIMER WAY ETERSBURG, VA 23803-8905 JSA CUSTOMER PURCHASE ORDER NUMBER 4500551339				SALES ORDER 12956968/0000			CUSTOMER MATERIAL Nº 000000003712650020			SPECIFICATION / DATE or REVI ASTM A6-17 ASTM A709-21 GR50 ASTM A992-20, A572-21 CSA G40.21-13 345WM, 50W			EVISION		
				BILL OF LADING 1330-0000198957				DATE 06/19/2023							
• , ,	овітіом (%) .13	P (%) 0.008	S (%) 0.037		Cu (%)	Ni (%)	Cr (%)	Mo(%) 0,040	Sn (%) 0.026	V (%) 0.002	Nb (%) 0.017	Al (% 0.003			
MECHANICAL PRO YS 0.2% (PS 53082	ECHANICAL PROPERTIES YS 0.2% (PSI) UTS (PSI)		70364				485		Y/T rati (%) 0.750 0.760	G/L (Inches) 8,000 8,000		G/L (mm) 200.0 200.0	E!	long. (%) 27.50 22.90	
COMMENTS / NOTE	F.S														
									n/metals-recycling. o		. I	day com			

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdau possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.

Mackey Quality Director

Phone: (409) 267-1071 Email: Bhaskar. Valamanchili@gerdau.com

alice L. Pitchford QUALITY ASSURANCE MGR.

Phone: (804) 524-2851 Email: Alice.pitchford@gerdau.com