

Order No./계약번호 : 01S6058370

PO No./주문번호 : 506774

Supplier /주문자 : POSCO INTERNATIONAL CORPORATION

Commodity /품명 : HOT ROLLED STEEL PLATE

Customer /고객사

Spec & Type /규격 : ASTM A36/A709-36

Size/치수	Product No. 제품번호	Quantity 수량	Weight 중량 (kg) (lb)	Heat No. 제강번호	Country of Melt & Pour	Position	Tensile Test 인장시험			Division	Chemical Composition/화학성분									
							YP (ksi)	TS (%)	EL (%)		C (%)	Si (%)	Mn (%)	P (%)	S (%)	Cr (%)	Ni (%)	Cu (%)	Mo (%)	
0.875"x96"x240"	PB79755601-5608	8	20,744 45,728	SB73303	KOR	T	45.0	69.0	31	L	0.1712	0.258	0.927	0.0108	0.0032	0.026	0.016	0.021	0.003	0
*** Sub Total (040) ***		8	20,744 (kg)	45,728 (lb)						P	0.1738	0.250	0.920	0.0105	0.0034	0.024	0.016	0.020	0.004	0
1"x96"x240"	PB79652101-2107	7	20,741 45,724	SB73084	KOR	T	42.8	67.6	31	L	0.1686	0.232	0.864	0.0085	0.0052	0.026	0.014	0.018	0.002	0
1"x96"x240"	PB79652201-2205	5	14,815 32,660	SB73084	KOR	T	42.8	67.6	31	P	0.1638	0.233	0.859	0.0087	0.0055	0.024	0.014	0.018	0.003	0
1"x96"x240"	PB79652701-2702	2	5,926 13,064	SB73084	KOR	T	42.8	67.6	31	L	0.1686	0.232	0.864	0.0085	0.0052	0.026	0.014	0.018	0.002	0
1"x96"x240"	PB79652706-2707	2	5,926 13,064	SB73084	KOR	T	42.8	67.6	31	P	0.1638	0.233	0.859	0.0087	0.0055	0.024	0.014	0.018	0.003	0
1"x96"x240"	PB79652801-2807	7	20,741 45,724	SB73084	KOR	T	42.8	67.6	31	L	0.1686	0.232	0.864	0.0085	0.0052	0.026	0.014	0.018	0.002	0
*** Sub Total (060) ***		23	68,149 (kg)	150,236 (lb)						P	0.1638	0.233	0.859	0.0087	0.0055	0.024	0.014	0.018	0.003	0
1.25"x96"x240"	PB79650701-0705	5	18,515 40,820	SB73084	KOR	T	43.9	66.7	32	L	0.1686	0.232	0.864	0.0085	0.0052	0.026	0.014	0.018	0.002	0
*** Sub Total (080) ***		5	18,515 (kg)	40,820 (lb)						P	0.1638	0.233	0.859	0.0087	0.0055	0.024	0.014	0.018	0.003	0
1.5"x96"x240"	PB79317602-7604	3	13,336 29,397	SB72525	KOR	T	44.1	67.2	31	L	0.1432	0.244	1.046	0.0156	0.0040	0.032	0.013	0.018	0.003	0
1.5"x96"x240"	PB79573602	1	4,445 9,799	SB72959	KOR	T	43.8	67.2	32	P	0.1407	0.242	1.051	0.0160	0.0041	0.032	0.013	0.018	0.003	0
*** Sub Total (070) ***		4	17,780 (kg)	39,196 (lb)						L	0.1403	0.233	1.086	0.0178	0.0048	0.032	0.013	0.012	0.002	0
1.75"x96"x240"	PB79616401-6403	3	15,555 34,293	SB72959	KOR	T	43.9	66.9	32	P	0.1446	0.234	1.063	0.0176	0.0042	0.032	0.012	0.012	0.004	0

* Position - T : Top, M : Middle, B : Bottom
* Tensile Test. Direction : Transversal, Gauge Length : 200 mm(Rectangular), YP Method : 0.2 % off-set
* Division - L : Ladle Analysis, P : Products Analysis
* Supply Condition : As-Rolled unless otherwise Heat Treated.

This material has been fully killed and made by basic oxygen process. This material is fine grained steel.
This material has been made by vacuum degassing process.
Test Certificate is issued according to ISO 10474/EN 10204 3.1.
We hereby certify that the material herein has been made in accordance with the order and above specific:

Legal sanction can be imposed on forging. Improper use of product can cause safety issues.

Surveyor To :

B.S. Kim