			CERTIFIED N	MATERIAL TEST	REPORT	<u>_</u>		-			Page 1 / 1
GÐ GERDAU									SHAPE / SIZE Flat Bar / 3/4 X 1		DOCUMENT ID: 0000148537
JS-ML-WILTON 500-2500 WEST 3RD STREET						LENGTH 20'00"					Г / ВАТСН 3498 /02
VILTON, IA 52778 JSA	SALES ORDER 12978830/000010			CUSTOMER MATERIAL N° 000000000102410020			SPECIFICATION / DATE or REVISION ASME SA36, ASTM A529-14 ASTM A6-19, A36-19, A572-21				
CUSTOMER PURCHASE ORDER NUMBER 4500551641		BILL OF LADING 1334-0000091341		DATE 05/31/2023		ASTM A709-18, AASHTO M270-15 CSA G40.20-13/G40.21-13					
CHEMICAL COMPOSITION C (%) Mn (%) P (%) S (%)		· · ·	Ni (%) Cr (%	· · · ·	V (%)	Nb (%)	Sn (%)				
0.13 0.58 0.015 0.028	0.20	0.22	0.18 0.24	4 0.065	0.022	0.011	0.009				
MECHANICAL PROPERTIES Elong. (%) G/L (Inches) 22.50 8.000 22.50 8.000	τ	JTS (PSI) 72237 72365	UTS (N 498 499	,	YS (PSI) 56209 56379		YS (MPa) 388 389				
GEOMETRIC CHARACTERISTICS R:R 41.05											
COMMENTS / NOTES											
his grade meets the requirements for the following grades: STM Grades: A36; A529-50; A572-50; A709-36; A709-5 SA Grades: 44W; 50W ASHTO Grades: M270-36; M270-50											

Gerdau's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling, or contact metalsrecycling@gerdau.com.

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdau possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.

Mackey BHASKAR YALAMANCHILI QUALITY DIRECTOR

Definition daniel k wells QUALITY ASSURANCE MGR.

Phone: (409) 267-1071 Email: Bhaskar.Yalamanchili@gerdau.com

Phone: (563) 279-1238 Email: Daniel.wells1@gerdau.com