



CMC STEEL ALABAMA
101 S 50TH STREET
BIRMINGHAM AL 35212-3525

CERTIFIED MILL TEST REPORT
For additional copies call
800-637-3227

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Marcus W. McCluney
Marcus W. McCluney - CMC Steel AL
Quality Assurance Manager

1SERIES-BPS®

HEAT NO.:1087506 SECTION: FLAT 5/8x12 20'0" 36/52955UM GRADE: ASTM A36-19/A529-19 Gr55 Plate ROLL DATE: 07/23/2023 MELT DATE: 07/13/2023 Cert. No.: 85522150 / 087506B750	S O L D T O	7855875182 7855872282	S H I P T O	Longview, TX 9037591859	Delivery#: 85522150 BOL#: 75522144 CUST PO#: 4500556104 CUST P/N: 1020120020 DLVRY LBS / HEAT: 4590,000 LB DLVRY PCS / HEAT: 9 EA
--	--------------------------------	--------------------------	--------------------------------	----------------------------	--

Characteristic	Value	Characteristic	Value	Characteristic	Value
C	0.16%	Elongation Gage Lgth test 1	8IN		
Mn	0.82%	Yield to tensile ratio test1	0.74		
P	0.012%	Yield Strength test 2	56.4ksi		
S	0.024%	Tensile Strength test 2	74.8ksi		
Si	0.17%	Elongation test 2	25%		
Cu	0.35%	Elongation Gage Lgth test 2	8IN		
Cr	0.16%	Yield to tensile ratio test2	0.75		
Ni	0.14%				
Mo	0.046%				
V	0.036%				
Cb	0.002%				
Sn	0.012%				
B	0.0003%				
Ti	0.001%				
N	0.0111%				
Carbon Eq A6	0.37%				
Carbon Eq A529	0.40%				
Yield Strength test 1	56.0ksi				
Tensile Strength test 1	76.1ksi				
Elongation test 1	25%				

The Following is true of the material represented by this MTR:
 *Material is fully killed and is Hot Rolled Steel
 *100% melted, rolled, and manufactured in the USA
 *EN10204 2004 3.1 compliant
 *Contains no weld repair
 *Contains no Mercury contamination
 *Manufactured in accordance with the latest version of the plant quality manual
 *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661
 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov

REMARKS : ALSO MEETS ASTM A36, A529 GR.50, A529 GR.55, A572 GR.50, A572 GR.55, A709 GR.36, A709 GR.50, AASHTO M270 GR.36, M270 GR.50, CSA G40.21-04 44 W, 50W,ASME SA-36 2008A ADDEND A