Atlas Tube Arkansas 6651 E Hwy 137 Blytheville Arkansas USA 72315 Tel:

Fax:



REF.B/L: 81169379 Date: 08/21/2023 Customer: 179

MATERIAL TEST REPORT

Material: 12.0x4.0x250x40'0"0(2x4). **Material No:** 1200402504000 Made in: **USA** Melted and Poured in: **USA Sales Order:** 1943189 **Purchase Order:** C452006319 Cust Material#: 66120040025040 С Ρ В **Heat No** Mn S Si ΑI Cu Cb Мо Ni Cr Τi Ν Ca 23114342 0.210 0.003 0.030 0.730 0.007 0.034 0.090 0.001 0.012 0.040 0.050 0.002 0.001 0.0001 0.0075 0.0019 **Bundle No PCs Yield Tensile** Eln.2in Certification CE: 0.36

M500479138 8 063418 Psi 075777 Psi 34 % ASTM A500-21 GRADE B&C

Heat MILL Mill Location Method Recycled Content Post Consumer Pre-Consumer (Post Industrial) % Harvested Within Miles of Location

23114342 BIGRIVER Osceola,AR EAF 76.00% 95.00% 5.00 % 75% 500

Material Note: Sales Or. Note:

Authorized by Quality Assurance: Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1



