



US-ML-MIDLOTHIAN
300 WARD ROAD
MIDLOTHIAN, TX 76065
USA

CERTIFIED MATERIAL TEST REPORT

CUSTOMER SHIP TO LONGVIEW, TX 75604-4817 USA		CUSTOMER BILL TO MANHATTAN, KS 66505-1688 USA		GRADE A992/A572-50	SHAPE / SIZE Wide Flange Beam / 12 X 53# / 310 X 79	DOCUMENT ID: 0000953566
SALES ORDER 13001405/000080		CUSTOMER MATERIAL N° 00000003712530020		LENGTH 20'00"	PCS 8	WEIGHT 8,480 LB
CUSTOMER PURCHASE ORDER NUMBER 4500552060		BILL OF LADING 1327-0000531823		DATE 06/08/2023		
SPECIFICATION / DATE or REVISION ASTM A6-17 ASTM A709-21 GR50 ASTM A992-20, A572-21 CSA G40.21-13 345WM, 50W						
HEAT / BATCH 59109648/05						

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Ni (%)	Cr (%)	Mo (%)	Sn (%)	V (%)	Nb (%)	Al (%)	CEqvA6 (%)
0.09	0.87	0.005	0.024	0.22	0.31	0.10	0.14	0.024	0.009	0.001	0.019	0.001	0.29

YS 0.2% (PSI)	UTS (PSI)	YS (MPa)	UTS (MPa)	Y/T rati (%)	G/L (Inches)	G/L (mm)	Elong. (%)
54392	69947	375	482	0.780	8.000	200.0	21.10
54261	68438	374	472	0.790	8.000	200.0	21.40

COMMENTS / NOTES

Gerdaul's steel is 100% recyclable. Support the circular economy through our Metals Recycling Partnership. For details, visit www2.gerdau.com/metals-recycling, or contact metalsrecycling@gerdau.com.

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdaul possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.

Bhaskar
BHASKAR YALAMANCHILI
QUALITY DIRECTOR
Phone: (409) 267-1071 Email: Bhaskar.Yalamanchili@gerdau.com

Wade Lumpkins
WADE LUMPKINS
QUALITY ASSURANCE MGR.
Phone: 972-779-3118 Email: Wade.Lumpkins@gerdau.com